



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
KOMATSU WA-200-5L RTL-1 (S/N 65707)
Component
Front Differential
Fluid
{not provided} (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		CL0005249	CL0004031	CL0000863
Sample Date		Client Info		11 Mar 2024	24 Feb 2023	04 Feb 2020
Machine Age	hrs	Client Info		9815	9460	8585
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>500	348	308	302
Chromium	ppm	ASTM D5185m	>10	5	4	4
Nickel	ppm	ASTM D5185m	>10	1	<1	<1
Titanium	ppm	ASTM D5185m		1	1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	6	5	6
Lead	ppm	ASTM D5185m	>25	<1	2	1
Copper	ppm	ASTM D5185m	>100	3	3	3
Tin	ppm	ASTM D5185m	>10	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION





There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	34	30	29
Potassium	ppm	ASTM D5185m	>20	2	0	1
Water		WC Method	>.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	VLITE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		2	5	4
Boron	ppm	ASTM D5185m		11	10	9
Barium	ppm	ASTM D5185m		<1	0	2
Molybdenum	ppm	ASTM D5185m		3	3	1
Manganese	ppm	ASTM D5185m		7	7	6
Magnesium	ppm	ASTM D5185m		13	19	13
Calcium	ppm	ASTM D5185m		3379	3106	3429
Phosphorus	ppm	ASTM D5185m		1162	980	1133
Zinc	ppm	ASTM D5185m		1355	1166	1231
Sulfur	ppm	ASTM D5185m		13791	12324	13828
Visc @ 40°C	cSt	ASTM D445		95.5	94.6	94.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : CL0005249
Lab Number : 06121808
Unique Number : 10935959
Test Package : CONST
Received : 18 Mar 2024
Tested : 19 Mar 2024
Diagnosed : 19 Mar 2024 - Wes Davis

BULLSEYE CONSTRUCTION
 581 N POLK ST
 PINEVILLE, NC
 US 28134
 Contact: SERVICE MANAGER

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: