



## VOLVO A45G 13411 (S/N 752029)


Component
Transmission (Auto)
Fluid


DEXRON III (--- GAL)

DEXRON III ( GAL)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		ASC0008685		
	Sample Date		Client Info		24 Feb 2024		
	Machine Age	hrs	Client Info		1328		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	nnm	ACTM DE10Em	. 160	E2		
WEAN	Iron	ppm	ASTM D5185m		52		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>5	6		
	Titanium Silver	ppm	ASTM D5185m	. 5	<1		
	Aluminum	ppm	ASTM D5185m		0 27		
	Lead	ppm	ASTM D5185m ASTM D5185m	>50	0		
	Copper	ppm	ASTM D5185m		44		
	Tin		ASTM D5185m		6		
	Vanadium	ppm	ASTM D5185m	>10	0		
	White Metal	ppm scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
<u> </u>		Scalai	visuai	INOINL			
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	15		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	4		
, in the second	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		4		
	Boron	ppm	ASTM D5185m		74		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		4		
	Magnesium	ppm	ASTM D5185m		1		
	Calcium	ppm	ASTM D5185m		81		
	Phosphorus	ppm	ASTM D5185m		188		
	Zinc	ppm	ASTM D5185m		6		
	Sulfur	ppm	ASTM D5185m		1876		
	Visc @ 40°C	cSt	ASTM D445	35.0	28.2		
Report Id: V/OI V/08769 [WI ISCAR] 06121843 (Generated: 03/21/2024 11:36:09) Rev: 1	=				n: ALLEN W		











Certificate L2367

Laboratory Sample No.

Lab Number : 06121843

: ASC0008685 Unique Number: 10935994 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 18 Mar 2024 : 21 Mar 2024 **Tested** Diagnosed

: 21 Mar 2024 - Jonathan Hester

117 - ASCENDUM MACHINERY INC - GREENVILLE

2002 N GREENE ST GREENVILLE, NC US 27834

Contact: ALLEN WILLIAMS

F: (704)494-8197

allen.williams@ascendummachinery.com T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)