



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 3032E 1LV3032EPLL134881

Component
Diesel Engine

Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0189844	JR0135489	JR0093507
Sample Date		Client Info		05 Mar 2024	07 Feb 2023	11 Jan 2022
Machine Age	hrs	Client Info		133	90	49
Oil Age	hrs	Client Info		0	90	0
Filter Age	hrs	Client Info		0	90	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>51	4	6	14
Chromium	ppm	ASTM D5185m	>11	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	2	3	4
Lead	ppm	ASTM D5185m	>26	0	<1	2
Copper	ppm	ASTM D5185m	>26	0	2	16
Tin	ppm	ASTM D5185m	>4	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	16	14	▲ 61
Potassium	ppm	ASTM D5185m	>20	0	<1	0
Fuel		WC Method	>2.1	<1.0	<1.0	0.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	6.6	6.9	7.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.1	19.4	20.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	<1	2	11
Boron	ppm	ASTM D5185m		254	274	213
Barium	ppm	ASTM D5185m		0	1	7
Molybdenum	ppm	ASTM D5185m		241	234	212
Manganese	ppm	ASTM D5185m		0	<1	1
Magnesium	ppm	ASTM D5185m		849	750	606
Calcium	ppm	ASTM D5185m		1426	1404	1739
Phosphorus	ppm	ASTM D5185m		902	822	863
Zinc	ppm	ASTM D5185m		1032	1017	1060
Sulfur	ppm	ASTM D5185m		3498	3466	3352
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.4	14.6	15.1
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	9.8	10.2	11.7
Visc @ 100°C	cSt	ASTM D445	15.4	13.1	13.4	● 11.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0189844 **Received** : 19 Mar 2024
Lab Number : 06122092 **Tested** : 19 Mar 2024
Unique Number : 10936243 **Diagnosed** : 19 Mar 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

JRE - LA CROSSE
 38431 HWY 58
 LA CROSSE, VA
 US 23950-1807

Contact: HUNTER GREEN
 hgreen@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (434)447-4325
 F: (434)447-1329