


WEAR CONTAMINATION **FLUID CONDITION** **NORMAL NORMAL NORMAL**

Machine Id **846-4897**

Component _							
Diesel Engine							
MOBIL DELVAC 1300 SUPER15W40 (QTS)							
	T		N 4 - 4	Line in /A leas			11:-10
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
No corrective action is recommended at this time. Resample at the next service interval to monitor. Please specify the component make and model with your next sample.	Sample Number		Client Info		RPL0015197		
	Sample Date	mala	Client Info		10 Jan 2024		
	Machine Age	mls	Client Info		47156		
	Oil Age Filter Age	mls	Client Info		60000 60000		
	Oil Changed	mls	Client Info				
	Filter Changed		Client Info		Changed Changed		
	Sample Status		Client inio		NORMAL		
					INUNIVIAL		
WEAR	Iron	ppm	ASTM D5185m	>100	63		
	Chromium	ppm	ASTM D5185m	>20	2		
Metal levels are typical for a new component breaking in.	Nickel	ppm	ASTM D5185m	>4	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	>3	<1		
	Aluminum	ppm	ASTM D5185m	>20	22		
	Lead	ppm	ASTM D5185m	>40	4		
	Copper	ppm	ASTM D5185m	>330	25		
	Tin	ppm	ASTM D5185m	>15	3		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
Fuel content negligible. Elevated aluminum (AI) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m		37		
	Potassium	ppm	ASTM D5185m		61		
	Fuel	%	ASTM D3524		0.4		
	Water		WC Method	>0.2	NEG		
	Glycol	0/	WC Method	0	NEG		
	Soot %	%	*ASTM D7844		0.4		
	Nitration	Abs/cm	*ASTM D7624	>20	10.7		
	Sulfation	Abs/.1mm	*ASTM D7415		22.7		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual		NONE NONE		
	Sand/Dirt	scalar	*Visual	NONE NORML			
	Appearance Odor	scalar	*Visual *Visual	NORML	NORML NORML		
	Emulsified Water	scalar		>0.2	NEG		
<u></u>		Scalai	*Visual	>0.2			
FLUID CONDITION	Sodium	ppm	ASTM D5185m		4		
	Boron	ppm	ASTM D5185m	0	19		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m	0	4		
	Molybdenum	ppm	ASTM D5185m	0	30		
	Manganese	ppm	ASTM D5185m		6		
	Magnesium	ppm	ASTM D5185m	0	838		
	Calcium	ppm	ASTM D5185m		1304		
	Phosphorus	ppm	ASTM D5185m		863		
	Zinc	ppm	ASTM D5185m		1054		
	Sulfur	ppm	ASTM D5185m		2993		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	19.9		
	Base Number (BN)	mg KOH/g	ASTM D2896	9.4	6.3		
	Visc @ 100°C	cSt	ASTM D445	14	12.1		







Report Id: PAC7013 [WUSCAR] 06122198 (Generated: 03/22/2024 22:47:59) Rev: 1

Laboratory Sample No.

Lab Number : 06122198 Unique Number: 10936349

: RPL0015197

Received **Tested** Diagnosed

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: 19 Mar 2024 : 22 Mar 2024

: 22 Mar 2024 - Wes Davis

901 64th St. N.W. Albuquerque, NM US 87121 Contact: Aaron Arrey

Test Package: FLEET (Additional Tests: FuelDilution, PercentFuel) To discuss this sample report, contact Customer Service at 1-800-237-1369. ArreyA@RushEnterprises.Com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (505)767-7404

Contact/Location: Aaron Arrey - PAC7013