



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
MONTGOMERY
Machine Id
MACK 420047
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0115590	GFL0088652	GFL0088662
Sample Date		Client Info		15 Mar 2024	27 Feb 2024	13 Feb 2024
Machine Age	hrs	Client Info		382	10227	1521
Oil Age	hrs	Client Info		750	595	1521
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	5	12	7
Chromium	ppm	ASTM D5185m	>20	<1	1	<1
Nickel	ppm	ASTM D5185m	>5	<1	<1	0
Titanium	ppm	ASTM D5185m	>2	<1	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	4	6	4
Lead	ppm	ASTM D5185m	>40	<1	<1	<1
Copper	ppm	ASTM D5185m	>330	<1	2	2
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	11	7
Potassium	ppm	ASTM D5185m	>20	3	5	6
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>4	0.1	0.3	0.3
Nitration	Abs/cm	*ASTM D7624	>20	5.5	8.0	7.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.0	19.2	18.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	4	0
Boron	ppm	ASTM D5185m	0	3	3	1
Barium	ppm	ASTM D5185m	0	0	0	3
Molybdenum	ppm	ASTM D5185m	60	80	66	59
Manganese	ppm	ASTM D5185m	0	<1	<1	0
Magnesium	ppm	ASTM D5185m	1010	1358	1033	881
Calcium	ppm	ASTM D5185m	1070	1487	1132	994
Phosphorus	ppm	ASTM D5185m	1150	1464	1086	999
Zinc	ppm	ASTM D5185m	1270	1828	1359	1155
Sulfur	ppm	ASTM D5185m	2060	5067	3302	3104
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.8	15.5	15.1
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.4	7.4	7.5
Visc @ 100°C	cSt	ASTM D445	15.4	13.9	13.4	13.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : GFL0115590

Lab Number : 06122208

Unique Number : 10936359

Test Package : FLEET

Received : 19 Mar 2024

Tested : 20 Mar 2024

Diagnosed : 21 Mar 2024 - Don Baldrige

GFL Environmental - 955 - Montgomery

1121 Wilbanks St

Montgomery, AL

US 36108

Contact: LISA REEVES

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: