

## 24C1102 PCMOEURO-375

## Component New (Unused) Oil

{not provided} (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
This is a baseline read-out on the submitted sample.	Sample Number		Client Info		HPL0001087		
	Sample Date		Client Info		11 Mar 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	lvan		ASTM D5185m		4		
	Iron	ppm			1		
	Chromium Nickel	ppm	ASTM D5185m		0		
		ppm	ASTM D5185m		0		
	Titanium Silver	ppm	ASTM D5185m ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m		4 <1		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm ppm	ASTM D5185m		۰ <1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		12		
	Potassium	ppm	ASTM D5185m	>20	0		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual		NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2		
	Boron	ppm	ASTM D5185m		76		
	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		521		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		899		
	Calcium	ppm	ASTM D5185m		2700		
	Phosphorus	ppm	ASTM D5185m		968		
	Zinc	ppm	ASTM D5185m		997		
	Sulfur	ppm	ASTM D5185m		9280		
	Base Number (BN)	mg KOH/g	ASTM D2896		15.15		
	Visc @ 40°C	cSt	ASTM D445		99.41		
	Visc @ 100°C	cSt	ASTM D445		15.17		
		0					

Viscosity Index (VI) Scale ASTM D2270

160



