

# WEAR NORMAL CONTAMINATION ABNORMAL FLUID CONDITION ABNORMAL

#### Machine Id MACK 152433

Component Diesel Engine

## DIESEL ENGINE OIL SAE 15W40 (40 QTS)

RECOMMENDATION

We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition. Please specify the brand, type, and viscosity of the oil on your next sample.

	_		
<b></b>			
	_		

All component wear rates are normal.

### CONTAMINATION

There is a moderate amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.

#### FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. Fuel is present in the oil and is lowering the viscosity. The oil is no longer serviceable due to the presence of contaminants.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0917977	WC0861039	WC0827114
Sample Date		Client Info		18 Mar 2024	27 Sep 2023	07 Jun 2023
Machine Age	mls	Client Info		104501	100525	96792
Oil Age	mls	Client Info		0	3733	4014
Filter Age	mls	Client Info		0	3733	4014
Oil Changed		Client Info		N/A	Changed	Changed
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				ABNORMAL	NORMAL	NORMAL
Iron	ppm	ASTM D5185m	>120	11	7	14
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	1	<1	1
Titanium	ppm	ASTM D5185m	>2	<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	5	4	4
Lead	ppm	ASTM D5185m	>40	0	<1	<1
Copper	ppm	ASTM D5185m	>330	<1	<1	1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Cilicon			. 05	А	4	7
Deteccium	ppm	AGTM DE105m	>20	4	4	1
Fotassium	ррп1 0/		>20	3	2	4
Fuel	70	ASTIVI D5524	>3.0	3.0 NEC	<1.0 NEC	<1.0
Chrool		WC Wethod	>0.2	NEG	NEG	NEG
Giycol Soot %	0/		. 1	NEG 0.5	NEG 0.4	NEG
SUUL %	70 Abo/om	*AGTM D7604	>4	10.0	0.4	10.6
Sulfation	Abs/CIII	*AGTM D7024	>20	01.9	3.7 20.1	21.7
Sullation	AUS/.IIIIII	*Vieual			20.1	NONE
Dobric	scalar	*Vicual	NONE	NONE	NONE	NONE
Sand/Dirt	coalar	*Visual	NONE	NONE	NONE	NONE
	scalar	*Vieual	NORM	NORMI	NORM	NORMI
Odor	scalar	*Visual	NORMI	NORMI	NORMI	NORMI
Emulsified Water	scalar	*Visual		NEG	NEG	NEG
	Jouran	VISUUI	20.L		NEG	NLG
Sodium	ppm	ASTM D5185m	>158	3	2	2
Boron	ppm	ASTM D5185m	250	22	21	28
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	51	50	50
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	450	691	684	742
Calcium	ppm	ASTM D5185m	3000	1214	1117	1136
Phosphorus	ppm	ASTM D5185m	1150	690	671	650
Zinc	ppm	ASTM D5185m	1350	848	851	868
Sulfur	ppm	ASTM D5185m	4250	2747	2688	2644
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.1	18.0	19.5
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	5.2	7.5	7.6

Visc @ 100°C cSt

ASTM D445 14.4

12.5

12.2

13.1



Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)