
WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

NOT GIVEN MW0037556 (S/N NO INFO ON SIF/BOTTLE)

Component Starboard Genset

Fluid

not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		MW0037556		
	Sample Date		Client Info		25 Feb 2024		
	Machine Age	hrs	Client Info		24185		
	Oil Age	hrs	Client Info		407		
	Filter Age	hrs	Client Info		407		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
VEAR	Iron	ppm	ASTM D5185m	>50	4		
WEATT.	Chromium	ppm	ASTM D5185m		0		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	>2	3		
				. =			
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m	>15	0		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	<1		
	Fuel		WC Method	>4.0	<1.0		
	Water		WC Method	>0.1	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844		0.2		
	Nitration	Abs/cm	*ASTM D7624	>20	7.9		
	Sulfation	Abs/.1mm	*ASTM D7415		19.1		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt		*Visual	NONE	NONE		
		scalar					
	Appearance Odor	scalar	*Visual	NORML	NORML NORML		
		scalar	*Visual	NORML	-		
<u> </u>	Emulsified Water	Scalar	*Visual	>0.1	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The BN result indicates that there is suitable alkalinity remaining in the	Boron	ppm	ASTM D5185m		183		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		83		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		566		
	Calcium	ppm	ASTM D5185m		2422		
	Phosphorus	ppm	ASTM D5185m		616		
	Zinc	ppm	ASTM D5185m		735		
	Sulfur	ppm	ASTM D5185m		3425		
			*ASTM D7414	- 25	14.4		
	()xidation	ADS/ IIIIII					
	Oxidation Base Number (BN)	Abs/.1mm		>25	8.0		







Certificate L2367

Laboratory Sample No.

Lab Number : 06123027 Unique Number: 10937178

: MW0037556

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 19 Mar 2024 : 20 Mar 2024 **Tested** Diagnosed

: 21 Mar 2024 - Don Baldridge

AMERICAN COMMERCIAL LINES

PO BOX 610, 1701 E. MARKET STREET JEFFERSONVILLE, IN

US 47130 Contact: RONALD SCHNEIDER

ronald.schneider@bargeacbl.com T:

Test Package : MAR 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (812)288-1644