



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
MARK DULEY
Machine Id
[MARK DULEY] 006 298357-6
Component
Starboard Reduction Gear
Fluid
CHEVRON MEROPA 320 (170 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0064402	MW0064264	MW0061623
Sample Date		Client Info		01 Mar 2024	06 Feb 2024	01 Jan 2024
Machine Age	hrs	Client Info		42571	42006	41144
Oil Age	hrs	Client Info		42571	42006	41144
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	71	68	69
Chromium	ppm	ASTM D5185m	>10	<1	<1	1
Nickel	ppm	ASTM D5185m	>10	0	<1	0
Titanium	ppm	ASTM D5185m		2	2	2
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	3	3	2
Lead	ppm	ASTM D5185m	>100	<1	2	2
Copper	ppm	ASTM D5185m	>50	32	31	34
Tin	ppm	ASTM D5185m	>10	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	9	9	8
Potassium	ppm	ASTM D5185m	>20	7	8	9
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	LIGHT
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		27	25	29
Boron	ppm	ASTM D5185m	20	13	16	13
Barium	ppm	ASTM D5185m		1	0	<1
Molybdenum	ppm	ASTM D5185m	0	4	0	0
Manganese	ppm	ASTM D5185m		1	<1	<1
Magnesium	ppm	ASTM D5185m		6	17	<1
Calcium	ppm	ASTM D5185m	25	40	54	33
Phosphorus	ppm	ASTM D5185m	235	187	203	192
Zinc	ppm	ASTM D5185m		42	57	41
Sulfur	ppm	ASTM D5185m		5314	5041	4700
Acid Number (AN)	mg KOH/g	ASTM D8045	0.56	1.24	1.06	1.01
Visc @ 40°C	cSt	ASTM D445	304	296	296	297



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW0064402

Lab Number : 06123238

Unique Number : 10937389

Test Package : MAR 2

Received : 19 Mar 2024

Tested : 20 Mar 2024

Diagnosed : 22 Mar 2024 - Jonathan Hester

INGRAM BARGE

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: JUSTIN WHEELER

justin.wheeler@ingrambarge.com

T:

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)