



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 50G 1FF050GXCHH286613
 Component
Hydraulic System
 Fluid
HITACHI HYDRAULIC SUPER EX 46HN (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0210875	JR0117374	JR0075870
Sample Date		Client Info		19 Mar 2024	11 Jan 2022	11 Jan 2021
Machine Age	hrs	Client Info		2615	2187	1583
Oil Age	hrs	Client Info		0	0	1583
Filter Age	hrs	Client Info		0	604	1583
Oil Changed		Client Info		Not Changed	Changed	Not Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	9	16	16
Iron	ppm	ASTM D5185m	>32	2	11	8
Chromium	ppm	ASTM D5185m	>9	0	<1	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	<1	0
Aluminum	ppm	ASTM D5185m	>9	0	<1	<1
Lead	ppm	ASTM D5185m	>28	0	<1	0
Copper	ppm	ASTM D5185m	>50	<1	2	2
Tin	ppm	ASTM D5185m	>5	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>11	0	2	1
Potassium	ppm	ASTM D5185m	>20	0	<1	<1
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	3173	9956	19427
Particles >6µm		ASTM D7647	>20000	541	1096	3042
Particles >14µm		ASTM D7647	>640	52	59	134
Particles >21µm		ASTM D7647	>160	15	17	26
Particles >38µm		ASTM D7647	>40	1	0	4
Particles >71µm		ASTM D7647	>10	0	0	4
Oil Cleanliness		ISO 4406 (c)	>23/21/16	19/16/13	20/17/13	21/19/14
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	0	2	1
Boron	ppm	ASTM D5185m		0	<1	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	<1	<1
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		0	2	<1
Calcium	ppm	ASTM D5185m		<1	10	7
Phosphorus	ppm	ASTM D5185m	827	495	349	353
Zinc	ppm	ASTM D5185m	0	31	68	60
Sulfur	ppm	ASTM D5185m	13	214	369	311
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.15	0.160	0.124
Visc @ 40°C	cSt	ASTM D445	47	47.4	45.9	45.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0210875 **Received** : 20 Mar 2024
Lab Number : 06124270 **Tested** : 21 Mar 2024
Unique Number : 10938421 **Diagnosed** : 23 Mar 2024 - Don Baldrige
Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - MANASSAS PARK
 9107 OWENS DRIVE
 MANASSAS PARK, VA
 US 20111

Contact: DON VEST
 dvest@jamesriverequipment.com

T: (703)631-8500

F: (703)631-4715