



TRAAP

Texas Refinery Advanced Analysis Program

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
KENWORTH T880 61 (S/N 1YKZP4TX6J5203445)

Component
Diesel Engine

Fluid
TRC MOLY XL PRO-SPEC IV XP 15W40 (11 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		TR06124385	TR06038758	TR05893941
Sample Date		Client Info		09 Mar 2024	25 Nov 2023	01 Jul 2023
Machine Age	mls	Client Info		280393	260472	250472
Oil Age	mls	Client Info		40000	20000	10000
Filter Age	mls	Client Info		10000	10000	10000
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	43	26	12
Chromium	ppm	ASTM D5185m	>20	1	1	<1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	5	3	1
Lead	ppm	ASTM D5185m	>40	12	7	<1
Copper	ppm	ASTM D5185m	>330	1	<1	<1
Tin	ppm	ASTM D5185m	>15	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	7	6	6
Potassium	ppm	ASTM D5185m	>20	0	<1	4
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	0.5	0.3
Nitration	Abs/cm	*ASTM D7624	>20	14.9	13.8	10.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	31.1	29.3	22.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		7	5	0
Boron	ppm	ASTM D5185m		9	12	12
Barium	ppm	ASTM D5185m		0	0	<1
Molybdenum	ppm	ASTM D5185m		136	132	136
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		107	104	99
Calcium	ppm	ASTM D5185m		4440	3938	3936
Phosphorus	ppm	ASTM D5185m		962	790	823
Zinc	ppm	ASTM D5185m		1133	1039	994
Sulfur	ppm	ASTM D5185m		4856	3928	3590
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.7	18.4	15.1
Base Number (BN)	mg KOH/g	ASTM D2896		9.48	9.35	12.63
Visc @ 100°C	cSt	ASTM D445		15.5	15.3	14.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : TR06124385
Lab Number : 06124385
Unique Number : 10938536
Test Package : MOB 2

Received : 20 Mar 2024
Tested : 21 Mar 2024
Diagnosed : 23 Mar 2024 - Don Baldrige

RUNDELL INC
 2465 STATE HWY 38
 DRAIN, OR
 US 97435
 Contact: BOB RUNDELL
 bobrundell@rundellinc.com

To discuss this sample report, contact Customer Service at 1-800-827-0711.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: