

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL ATTENTION


Area

[W05004101]
Wachine Id
VOLVO A45G 342679

Component Rear Axle

GEAR OIL SAE 80W140 (10 GAL)

GEAR OIL SAE 80W140 (10 GA	L)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
The oil change at the time of sampling has been noted. Resample at the next service interval to monitor. (Customer Sample Comment:	Sample Number		Client Info		WC0886330	VCP362960	
	Sample Date		Client Info		19 Mar 2024	09 May 2022	
W05004101)	Machine Age	hrs	Client Info		8663	4641	
	Oil Age	hrs	Client Info		2000	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				ATTENTION	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	>900	69	196	
	Chromium	ppm	ASTM D5185m	>20	0	3	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0	<1	
	Titanium	ppm	ASTM D5185m		0	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>30	0	<1	
	Lead	ppm	ASTM D5185m	>50	0	0	
	Copper	ppm	ASTM D5185m	>150	<1	3	
	Tin	ppm	ASTM D5185m	>20	0	<1	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon		ACTM DE10Em	. 50	.4	A	
	Potassium	ppm	ASTM D5185m ASTM D5185m	>20	<1 0	0	
There is no indication of any contamination in the oil.	Water	ppm	WC Method		NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water		*Visual	>0.2	NEG	NEG	
ELUID CONDITION							
FLUID CONDITION	Sodium	ppm	ASTM D5185m	100	0	1	
The oil viscosity is lower than normal. Confirm oil type.	Boron	ppm	ASTM D5185m		272	198	
	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m	12	0	4	
	Magnesium	ppm	ASTM D5185m ASTM D5185m	10	<1	6	
	Magnesium Calcium	ppm	ASTM D5185m		<1 30	112	
	Phosphorus	ppm	ASTM D5185m		2348	1123	
	Zinc	ppm	ASTM D5185m		2346 10	27	
	Sulfur	ppm	ASTM D5185m		33011	25056	
	Visc @ 40°C	cSt	ASTM D3163III		58.9	290	
	1.00 @ 40 0	000	. 10 1111 0 110		(





Certificate L2367

Laboratory Sample No.

: WC0886330 Lab Number : 06124426 Unique Number: 10938577 Test Package : MOBCE

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested**

: 20 Mar 2024 : 21 Mar 2024 : 23 Mar 2024 - Don Baldridge Diagnosed

MCCLUNG-LOGAN EQUIPMENT CO - MANASSAS

8450 QUARRY ROAD MANASSAS, VA US 20110

Contact: MIKE MAYHUGH

MMAYHUGH@MCCLUNG-LOGAN.COM

T: (703)393-7344

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (703)393-7844