



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
IAN
Machine Id
IAN
Component
Port Reduction Gear
Fluid
CHEVRON MEROPA 320 (200 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0065480	MW0051017	MW0050879
Sample Date		Client Info		22 Jan 2024	22 Oct 2023	02 Oct 2023
Machine Age	hrs	Client Info		15026	79121	12470
Oil Age	hrs	Client Info		15026	12950	12470
Filter Age	hrs	Client Info		0	0	12470
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		None	None	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>150	150	137	143
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	3	<1	1
Lead	ppm	ASTM D5185m	>100	2	<1	2
Copper	ppm	ASTM D5185m	>50	27	22	24
Tin	ppm	ASTM D5185m	>10	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	3	1	2
Potassium	ppm	ASTM D5185m	>20	10	6	7
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		44	39	42
Boron	ppm	ASTM D5185m	20	5	4	4
Barium	ppm	ASTM D5185m		2	0	0
Molybdenum	ppm	ASTM D5185m	0	<1	0	0
Manganese	ppm	ASTM D5185m		1	1	2
Magnesium	ppm	ASTM D5185m		3	3	0
Calcium	ppm	ASTM D5185m	25	20	8	10
Phosphorus	ppm	ASTM D5185m	235	175	196	190
Zinc	ppm	ASTM D5185m		32	21	26
Sulfur	ppm	ASTM D5185m		5323	5216	5431
Acid Number (AN)	mg KOH/g	ASTM D8045	0.56	0.86	0.63	0.74
Visc @ 40°C	cSt	ASTM D445	304	332	330	330



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0065480
Lab Number : 06125102
Unique Number : 10939253
Test Package : MAR 2

Received : 21 Mar 2024
Tested : 25 Mar 2024
Diagnosed : 25 Mar 2024 - Don Baldrige

AMERICAN RIVER TRANSPORTATION CO.
P.O. BOX 2889
ST. LOUIS, MO
US 63111
Contact: BRIAN GRIEWING
brian.griewing@adm.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: (314)481-5278