WEAR CONTAMINATION **FLUID CONDITION**


ATTENTION ABNORMAL NORMAL



JOHN DEERE 700J T0700JX116791

Left Final Drive

TDTO FLUID SAE 30 (QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
We advise that you check all areas where dirt can enter the system. The oil change at the time of sampling has been noted. Resample at the next service interval to monitor.	Sample Number		Client Info		JR0208771	JR0103309	
	Sample Date		Client Info		20 Mar 2024	10 Nov 2021	
	Machine Age	hrs	Client Info		5377	5377	
	Oil Age	hrs	Client Info		5377	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				ABNORMAL	SEVERE	
WEAR	PQ		ASTM D8184	>1250	392	269	
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	368	▲ 1422	
	Chromium	ppm	ASTM D5185m	>9	3	<u> </u>	
	Nickel	ppm	ASTM D5185m	>10	1	5	
	Titanium	ppm	ASTM D5185m		4	9	
	Silver	ppm	ASTM D5185m		0	1	
	Aluminum	ppm	ASTM D5185m	>40	<u>21</u>	7 5	
	Lead	ppm	ASTM D5185m	>15	0	<1	
	Copper	ppm	ASTM D5185m	>40	1	4	
	Tin	ppm	ASTM D5185m	>10	0	0	
	Vanadium	ppm	ASTM D5185m		<1	<1	
	White Metal	scalar	*Visual	NONE	MODER	VLITE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION Elemental levels of silicon (Si) and aluminum (Al) indicate aluminasilicate (coarse dirt) ingress.	Silicon	ppm	ASTM D5185m	>75	<u> </u>	▲ 556	
	Potassium	ppm	ASTM D5185m	>20	7	17	
	Water		WC Method	>0.075	NEG	NEG	
	Silt	scalar	*Visual	NONE	MODER	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0	<1	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		91	6	
	Barium	ppm	ASTM D5185m		1	0	
	Molybdenum	ppm	ASTM D5185m	5	2	8	
	Manganese	ppm	ASTM D5185m		3	13	
	Magnesium	ppm	ASTM D5185m		13	0	
	Calcium	ppm	ASTM D5185m		328	3416	
	Phosphorus	ppm	ASTM D5185m		915	1240	
	Zinc	ppm	ASTM D5185m		155	1279	
	Sulfur	ppm	ASTM D5185m		20912	4112	
	Visc @ 40°C	cSt	ASTM D445	101	126	105	





Laboratory Sample No.

: JR0208771 Lab Number : 06125146 Unique Number: 10939297

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 21 Mar 2024 : 25 Mar 2024 Tested

Diagnosed

: 25 Mar 2024 - Sean Felton

JRE - GREENVILLE 3604 HIGHWAY 264 E GREENVILLE, NC US 27834-5800 Contact: GREENVILLE SHOP

Test Package : CONST (Additional Tests: PQ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

christopher.martin@jamesriverequipment.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: