



Area **Ascendum Machinery** VOLVO EC300E 300E316668 Component Left Travel

VOLVO PREMIUM GEAR OIL 85W-140 GL-5 (--- GAL)

		<u> </u>					
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		ASC0005076		
resample at the next service interval to monitor.	Sample Date		Client Info		18 Mar 2024		
	Machine Age	hrs	Client Info		1969		
	Oil Age	hrs	Client Info		1969		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR				1000	470		
WEAR	Iron Chromium	ppm	ASTM D5185m ASTM D5185m		476 15		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	>0	0 <1		
	Silver	ppm ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>100	13		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	MODER		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>100	44		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		6		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	MODER		
	Debris	scalar	*Visual *Visual	NONE	NONE		
	Sand/Dirt Appearance	scalar	*Visual	NONE NORML	NONE NORML		
	Odor	scalar scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.25	NEG		
			v 150ai	20.25			
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	111	0		
	Barium	ppm	ASTM D5185m	0.0	5		
	Molybdenum	ppm	ASTM D5185m	0.9	0		
	Manganese	ppm	ASTM D5185m	0.0	7		
	Magnesium	ppm	ASTM D5185m		0		
	Calcium	ppm	ASTM D5185m		6		
	Phosphorus	ppm	ASTM D5185m		345		
	Zinc	ppm	ASTM D5185m	104	10		
	Sulfur	ppm	ASTM D5185m	20179	19874		


Visc @ 40°C

cSt

ASTM D445 333

Submitted By: CLAYTON SMITH

172



Ferrous Alloys 500 450 400 350 300 la 250 200 150 100 50 C far18/74 Non-ferrous Metals 10 lead maa Viscosity @ 40°C 420 400 380 360 340 320 300 () 280 र्ग रहु 260 240 220 200 180 160 Abnorma 140-120 Mar18/24 Mar18/24



MIDSOUTH LAND SERVICES Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : ASC0005076 Received : 21 Mar 2024 138 HILLCREST DR Lab Number : 06125195 Tested : 25 Mar 2024 ADVANCE, NC Unique Number : 10939346 Diagnosed : 25 Mar 2024 - Sean Felton Test Package : CONST Contact: Service Manager Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F:

Report Id: MIDADV [WUSCAR] 06125195 (Generated: 03/25/2024 13:48:26) Rev: 1

US 27006

Submitted By: CLAYTON SMITH

Page 2 of 2