



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
X48 (S/N MHMR3370)

Component
Diesel Engine

Fluid
VALVOLINE PREMIUM BLUE 2000 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0885549	WC0849039	WC0793100
Sample Date		Client Info		15 Mar 2024	22 Nov 2023	15 Jul 2023
Machine Age	hrs	Client Info		2857	2040	1347
Oil Age	hrs	Client Info		817	693	538
Filter Age	hrs	Client Info		817	693	538
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	56	31	14
Chromium	ppm	ASTM D5185m	>20	2	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	4	2	1
Lead	ppm	ASTM D5185m	>40	<1	0	0
Copper	ppm	ASTM D5185m	>330	2	<1	<1
Tin	ppm	ASTM D5185m	>15	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	7	4	3
Potassium	ppm	ASTM D5185m	>20	3	48	<1
Fuel		WC Method	>5	<1.0	<1.0	0.9
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	0.0	NEG
Soot %	%	*ASTM D7844	>3	1.3	0.9	0.5
Nitration	Abs/cm	*ASTM D7624	>20	10.9	9.8	9.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.8	21.4	20.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		6	6	3
Boron	ppm	ASTM D5185m		51	27	28
Barium	ppm	ASTM D5185m		<1	0	<1
Molybdenum	ppm	ASTM D5185m		87	90	46
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		1203	738	810
Calcium	ppm	ASTM D5185m		1895	1301	1182
Phosphorus	ppm	ASTM D5185m		1238	745	748
Zinc	ppm	ASTM D5185m		1418	897	895
Sulfur	ppm	ASTM D5185m		4251	2233	2739
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.7	17.7	18.3
Base Number (BN)	mg KOH/g	ASTM D2896	10.0	6.3	7.0	8.4
Visc @ 100°C	cSt	ASTM D445	15.2	13.4	13.0	13.6



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0885549 **Received** : 21 Mar 2024
Lab Number : **06125416** **Tested** : 22 Mar 2024
Unique Number : 10939567 **Diagnosed** : 25 Mar 2024 - Don Baldrige
Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

TULLY CONSTRUCTION BOULEVARD
 127-50 NORTHERN BLVD
 FLUSHING, NY
 US 11368
 Contact: MATT FLYNN
 Mflynn@tullyconstruction.com
 T: (917)299-4960
 F: