



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
912078
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (10 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0104539	GFL0041819	---
Sample Date		Client Info		22 Jan 2024	25 Jun 2022	---
Machine Age	hrs	Client Info		1095	1095	---
Oil Age	hrs	Client Info		600	600	---
Filter Age	hrs	Client Info		600	600	---
Oil Changed		Client Info		Changed	Changed	---
Filter Changed		Client Info		Changed	Changed	---
Sample Status				NORMAL	NORMAL	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	8	22	---
Chromium	ppm	ASTM D5185m	>20	<1	<1	---
Nickel	ppm	ASTM D5185m	>5	<1	3	---
Titanium	ppm	ASTM D5185m	>2	<1	0	---
Silver	ppm	ASTM D5185m	>2	0	1	---
Aluminum	ppm	ASTM D5185m	>20	2	2	---
Lead	ppm	ASTM D5185m	>40	<1	1	---
Copper	ppm	ASTM D5185m	>330	2	59	---
Tin	ppm	ASTM D5185m	>15	<1	2	---
Vanadium	ppm	ASTM D5185m		0	0	---
White Metal	scalar	*Visual	NONE	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	---

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	3	11	---
Potassium	ppm	ASTM D5185m	>20	2	0	---
Fuel		WC Method	>3.0	<1.0	<1.0	---
Water		WC Method	>0.2	NEG	NEG	---
Glycol		WC Method		NEG	NEG	---
Soot %	%	*ASTM D7844	>4	0.4	0.6	---
Nitration	Abs/cm	*ASTM D7624	>20	7.2	7.7	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.6	20.3	---
Silt	scalar	*Visual	NONE	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	3	---
Boron	ppm	ASTM D5185m	0	3	17	---
Barium	ppm	ASTM D5185m	0	0	0	---
Molybdenum	ppm	ASTM D5185m	60	60	64	---
Manganese	ppm	ASTM D5185m	0	0	<1	---
Magnesium	ppm	ASTM D5185m	1010	913	914	---
Calcium	ppm	ASTM D5185m	1070	1121	1182	---
Phosphorus	ppm	ASTM D5185m	1150	1046	913	---
Zinc	ppm	ASTM D5185m	1270	1220	1181	---
Sulfur	ppm	ASTM D5185m	2060	2903	3031	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.7	15.5	---
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.0	8	---
Visc @ 100°C	cSt	ASTM D445	15.4	13.7	13.3	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0104539
Lab Number : 06125478
Unique Number : 10939629
Test Package : FLEET

Received : 21 Mar 2024
Tested : 22 Mar 2024
Diagnosed : 22 Mar 2024 - Wes Davis

GFL Environmental - 461 - Smith Hauling
 3239 W. M 28
 Brimley, MI
 US 49715

Contact: Jim Smith
 jim.smith@gflenv.com

T: (906)635-3380

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)