



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
243 (S/N 1XK1D40X8KJ371776)
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0893939	WC0867911	WC0804077
Sample Date		Client Info		09 Apr 2024	26 Dec 2023	26 Jun 2023
Machine Age	mls	Client Info		0	0	0
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ABNORMAL	SEVERE

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	35	54	54
Chromium	ppm	ASTM D5185m	>20	5	4	2
Nickel	ppm	ASTM D5185m	>4	2	2	1
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	<1	<1	0
Aluminum	ppm	ASTM D5185m	>20	4	4	3
Lead	ppm	ASTM D5185m	>40	3	6	▲ 130
Copper	ppm	ASTM D5185m	>330	4	16	10
Tin	ppm	ASTM D5185m	>15	2	6	4
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	13	▲ 30	5
Potassium	ppm	ASTM D5185m	>20	3	6	2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	0.7	0.8
Nitration	Abs/cm	*ASTM D7624	>20	10.9	11.9	16.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.3	24.8	36.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>216	3	2	2
Boron	ppm	ASTM D5185m	250	11	11	18
Barium	ppm	ASTM D5185m	10	1	17	0
Molybdenum	ppm	ASTM D5185m	100	70	71	61
Manganese	ppm	ASTM D5185m		2	6	<1
Magnesium	ppm	ASTM D5185m	450	741	405	1003
Calcium	ppm	ASTM D5185m	3000	1429	1865	1261
Phosphorus	ppm	ASTM D5185m	1150	1089	1040	977
Zinc	ppm	ASTM D5185m	1350	1301	1324	1280
Sulfur	ppm	ASTM D5185m	4250	3474	3075	3335
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.0	23.0	44.5
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	5.4	4.6	▲ 2.9
Visc @ 100°C	cSt	ASTM D445	14.4	12.9	13.0	15.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0893939 **Received** : 10 Apr 2024
Lab Number : 06145216 **Tested** : 11 Apr 2024
Unique Number : 10970024 **Diagnosed** : 11 Apr 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

MANGUMS INC
 P.O. BOX 7177
 WILSON, NC
 US 27895
 Contact: ALAN BAGLEY
 alanb@mangumsinc.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: