

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL




Store 9 - Marietta Machine Id JOHN DEERE 672G 1DW672GXPLF708406


Rear Axle


JOHN DEERE HY-GARD HYD/TRANS (10 GAL)

	· · · · · · · · · · · · · · · · · · ·						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0049677		
'	Sample Date		Client Info		05 Apr 2024		
	Machine Age	hrs	Client Info		2403		
	Oil Age	hrs	Client Info		2403		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAD	DO				~-		,
WEAR	PQ		ASTM D8184	750	65		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		111		
	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	<u>\</u> 31	5		
	Potassium	ppm	ASTM D5185m	>20	2		
There is no indication of any contamination in the oil.	Water	ppm	WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	31		
	Barium	ppm	ASTM D5185m	0	1		
	Molybdenum	ppm	ASTM D5185m	0	24		
	Manganese	ppm	ASTM D5185m		4		
	Magnesium	ppm	ASTM D5185m	145	140		
	Calcium	ppm	ASTM D5185m	3570	2573		
	Phosphorus	ppm	ASTM D5185m	1290	915		
	Zinc	ppm	ASTM D5185m	1640	1003		
	Sulfur	ppm	ASTM D5185m		3166		
	Visc @ 40°C	cSt	ASTM D445	57.0	63.3		

63.3 --- ---Submitted By: JOHN MARTIN







Submitted By: JOHN MARTIN Page 2 of 2