



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
[W51086]

Machine Id
JOHN DEERE 75G 1FF075GXVFJ015758

Component
Diesel Engine

Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0179292	JR0180794	JR0106347
Sample Date		Client Info		09 Apr 2024	23 Oct 2023	03 Jun 2022
Machine Age	hrs	Client Info		4944	4854	4484
Oil Age	hrs	Client Info		0	0	500
Filter Age	hrs	Client Info		0	0	500
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	7	10	17
Chromium	ppm	ASTM D5185m	>11	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	<1	0	<1
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	4	6	6
Lead	ppm	ASTM D5185m	>26	<1	0	<1
Copper	ppm	ASTM D5185m	>26	<1	<1	<1
Tin	ppm	ASTM D5185m	>4	<1	<1	2
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	9	13	13
Potassium	ppm	ASTM D5185m	>20	1	0	0
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.4	0.5
Nitration	Abs/cm	*ASTM D7624	>20	7.0	9.4	9.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.0	22.5	23.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	1	3	1
Boron	ppm	ASTM D5185m		277	217	256
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		244	247	215
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		847	867	726
Calcium	ppm	ASTM D5185m		1467	1419	1459
Phosphorus	ppm	ASTM D5185m		947	776	830
Zinc	ppm	ASTM D5185m		1128	1111	1062
Sulfur	ppm	ASTM D5185m		3764	2927	2941
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.2	17.9	18.2
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	9.8	8.6	9.3
Visc @ 100°C	cSt	ASTM D445	15.4	14.2	14.5	14.6



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0179292 **Received** : 11 Apr 2024
Lab Number : 06145570 **Tested** : 12 Apr 2024
Unique Number : 10970378 **Diagnosed** : 12 Apr 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

JRE - ASHLAND
 11047 LEADBETTER RD
 ASHLAND, VA
 US 23005
 Contact: DAVID ZIEG
 dzieg@jamesriverequipment.com
 T: (804)798-6001
 F: (804)798-0292

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)