
WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

Machine Id BUS 754
Component
Diesel Engine

CHEVRON DELO 400 LE 15W40 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. WEAR	Sample Number		Client Info		DC0031947	DC0028367	
	Sample Date		Client Info		01 Apr 2024	23 Jun 2023	
	Machine Age	mls	Client Info		39855	11666	
	Oil Age	mls	Client Info		0	0	
	Filter Age	mls	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		Changed	Changed	
	Sample Status				NORMAL	ATTENTION	
	Iron	ppm	ASTM D5185m	>100	20	49	
	Chromium	ppm	ASTM D5185m		<1	2	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		<1	<1	
	Titanium	ppm	ASTM D5185m		<1	<1	
	Silver	ppm	ASTM D5185m	>3	0	0	
	Aluminum	ppm	ASTM D5185m		2	3	
	Lead	ppm	ASTM D5185m		- <1	<1	
	Copper	ppm	ASTM D5185m		<1	5	
	Tin	ppm	ASTM D5185m		<1	<1	
	Vanadium	ppm	ASTM D5185m		<1	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m		7	16	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		1	4	
	Fuel		WC Method		<1.0	0.5	
	Water		WC Method	>0.2	NEG	NEG	
	Glycol		WC Method	-	NEG	NEG	
	Soot %	%	*ASTM D7844		0.3	0.5	
	Nitration	Abs/cm	*ASTM D7624	>20	7.5	9.6	
	Sulfation	Abs/.1mm	*ASTM D7415		21.4	22.5	
	Silt Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE NONE	NONE NONE	NONE NONE	
	Appearance	scalar scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water		*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		6	4	
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		308	60	
	Barium	ppm	ASTM D5185m		<1	7	
	Molybdenum	ppm	ASTM D5185m		83	44	
	Manganese	ppm	ASTM D5185m		<1	2	
	Magnesium	ppm	ASTM D5185m		409	522	
	Calcium	ppm	ASTM D5185m		1495	1646	
	Phosphorus	ppm	ASTM D5185m		1035	752	
	Zinc	ppm	ASTM D5185m	1300	1290	944	
	Sulfur	ppm	ASTM D5185m		3757	2824	
	Oxidation	Abs/.1mm	*ASTM D7414		15.2	20.9	
	Base Number (BN)	mg KOH/g	ASTM D2896	9.6	6.6	9.1	
	Visc @ 100°C	cSt	ASTM D445	15.7	13.3	11.8	





Certificate L2367

Laboratory Sample No.

Lab Number : 06145628

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : DC0031947

Unique Number : 10970436 Test Package : MOB 1 (Additional Tests: TBN)

Received **Tested** Diagnosed

: 11 Apr 2024 : 12 Apr 2024

: 14 Apr 2024 - Don Baldridge

4472 GALLANT GREEN RD WALDORF, MD US 20601 Contact: Paul Or Larry Lking@kellerbus.com

T: (301)645-5734 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)