
**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL NORMAL NORMAL** 

## TPR-Houston Port

6354 6354
Component Axle

CHEVRON 1000 THF ( GAL)							
Resample at the next service interval to monitor. Please specify the component make and model with your next sample.	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		DJJ0023640	DJJ0023560	DJJ0018945
	Sample Date		Client Info		05 Apr 2024	19 Feb 2024	13 Nov 2023
	Machine Age	hrs	Client Info		17890	17614	16443
	Oil Age	hrs	Client Info		500	1000	0
	Filter Age	hrs	Client Info		500	1000	0
	Oil Changed		Client Info		Not Changd	Changed	N/A
	Filter Changed		Client Info		Not Changd	Changed	N/A
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR	Iron	ppm	ASTM D5185m	>500	10	13	17
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	0	0	0
	Nickel	ppm	ASTM D5185m	>10	0	0	0
	Titanium	ppm	ASTM D5185m		0	0	0
	Silver	ppm	ASTM D5185m		0	0	0
	Aluminum	ppm	ASTM D5185m	>25	0	0	0
	Lead	ppm	ASTM D5185m	>25	0	<1	0
	Copper	ppm	ASTM D5185m	>50	0	1	<1
	Tin	ppm	ASTM D5185m	>10	0	0	0
	Vanadium	ppm	ASTM D5185m		0	<1	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	5	4	6
	Potassium	ppm	ASTM D5185m		0	0	0
There is no indication of any contamination in the oil.	Water	1-1-	WC Method	>0.2	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1	1	<1
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	10	9	13	24
	Barium	ppm	ASTM D5185m		0	0	0
	Molybdenum	ppm	ASTM D5185m		4	5	9
	Manganese	ppm	ASTM D5185m		0	<1	0
	Magnesium	ppm	ASTM D5185m	20	26	22	49
	Calcium	ppm	ASTM D5185m		2654	2504	2496
	Phosphorus	ppm	ASTM D5185m		980	990	965
	Zinc	ppm	ASTM D5185m		1151	1100	1115
	Sulfur	ppm	ASTM D5185m		4033	3475	3537
	Visc @ 40°C	cSt	ASTM D445	58.4	53.5	51.9	53.7





Certificate L2367

Laboratory

Sample No.

: DJJ0023640 Lab Number : 06146191 Unique Number: 10976269

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** 

Diagnosed Test Package : MOBCE

: 11 Apr 2024

: 12 Apr 2024

: 12 Apr 2024 - Wes Davis

**TEXAS PORT RECYCLING - HOUSTON PORT** 

8945 MANCHESTER ST HOUSTON, TX

US 77012 Contact: Dale Shaw

dale.shaw@tmrecycling.com T:

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (713)921-5545

Contact/Location: Dale Shaw - TEXHOUWC