

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL

Ascendum Machinery Machine Id VOLVO L180H 5676 Component Rear Axle Fluid VOLVO WB 102 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

WEAR

All component wear rates are normal.

CONTAMINATION

There is no indication of any contamination in the oil.

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ASC0007055		
Sample Date		Client Info		09 Apr 2024		
Machine Age	hrs	Client Info		453		
Oil Age	hrs	Client Info		453		
Filter Age	hrs	Client Info		453		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		Changed		
Sample Status				NORMAL		
Iron		ASTM D5185m	>500	19		
Chromium	ppm			-		
	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>30	<1		
Lead	ppm	ASTM D5185m	>50	0		
Copper	ppm	ASTM D5185m	>120	<1		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m		0		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>50	8		
Potassium	ppm	ASTM D5185m	>20	<1		
Water	ppm	WC Method	>0.2	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Sodium	ppm	ASTM D5185m		10		
Boron	ppm	ASTM D5185m		118		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		2		
Manganese	ppm	ASTM D5185m		2		
Magnesium	ppm	ASTM D5185m		9		
Calcium	ppm	ASTM D5185m		3709		
Phosphorus	ppm	ASTM D5185m		1283		
Zinc	ppm	ASTM D5185m		1536		
Sulfur	ppm	ASTM D5185m		4621		
	0°t	ASTM D445		/10		


Visc @ 40°C


cSt

ASTM D445 55

Submitted By: SONNY POPE

41.9







METAL RECYCLING SERVICES - MONROE P.O. BOX 812 MONROE, NC : 12 Apr 2024 - Wes Davis US 28111 Contact: RYAN BOWDEN

Test Package : CONST To discuss this sample report, contact Customer Service at 1-800-237-1369.

: ASC0007055

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (704)238-0755

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received

Diagnosed

Tested

: 11 Apr 2024

: 12 Apr 2024

Certificate L2367

Laboratory

Sample No.

Lab Number : 06146205

Unique Number : 10976283

Submitted By: SONNY POPE Page 2 of 2

T: