



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
CATERPILLAR 938K F-47
Component
Diesel Engine
Fluid
DURAMAX 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DC0020449	DC0024235	DC0029742
Sample Date		Client Info		07 Dec 2023	20 Oct 2023	01 Sep 2023
Machine Age	hrs	Client Info		18577	18281	17980
Oil Age	hrs	Client Info		296	301	330
Filter Age	hrs	Client Info		296	301	330
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	7	16	17
Chromium	ppm	ASTM D5185m	>20	0	0	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	<1
Titanium	ppm	ASTM D5185m	>2	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>25	4	3	3
Lead	ppm	ASTM D5185m	>40	0	0	<1
Copper	ppm	ASTM D5185m	>330	12	104	<1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	4	6	5
Potassium	ppm	ASTM D5185m	>20	1	▲ 22	5
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	6.4	7.4	6.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.3	15.8	15.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		5	▲ 315	6
Boron	ppm	ASTM D5185m		4	3	3
Barium	ppm	ASTM D5185m		0	0	11
Molybdenum	ppm	ASTM D5185m		4	35	8
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m		54	49	88
Calcium	ppm	ASTM D5185m		2254	2234	2209
Phosphorus	ppm	ASTM D5185m		934	895	899
Zinc	ppm	ASTM D5185m		1058	1054	1085
Sulfur	ppm	ASTM D5185m		4300	4419	3695
Oxidation	Abs/.1mm	*ASTM D7414	>25	9.3	9.1	8.8
Base Number (BN)	mg KOH/g	ASTM D2896		7.2	11.83	7.2
Visc @ 100°C	cSt	ASTM D445		13.6	14.2	13.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DC0020449 **Received** : 11 Apr 2024
Lab Number : 06146447 **Tested** : 12 Apr 2024
Unique Number : 10976525 **Diagnosed** : 12 Apr 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

THOMAS BENNETT & HUNTER INC
 70 JOHN ST
 WESTMINSTER, MD
 US 21157
 Contact: JOE STEPHAN
 jstephan@tbhconcrete.com
 T: (410)848-9030
 F: (410)848-9032

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)