



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
INTERNATIONAL HV613 A-423
Component
Diesel Engine
Fluid
DURAMAX 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DC0032173	DC0025551	DC0025545
Sample Date		Client Info		10 Feb 2024	29 Jul 2023	13 May 2023
Machine Age	hrs	Client Info		4518	3140	2599
Oil Age	hrs	Client Info		658	541	694
Filter Age	hrs	Client Info		658	541	694
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	13	13	19
Chromium	ppm	ASTM D5185m	>20	<1	1	1
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	5	1
Lead	ppm	ASTM D5185m	>40	0	0	0
Copper	ppm	ASTM D5185m	>330	4	2	7
Tin	ppm	ASTM D5185m	>15	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	7	10	11
Potassium	ppm	ASTM D5185m	>20	4	8	7
Fuel		WC Method	>2.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.8	0.5	0.7
Nitration	Abs/cm	*ASTM D7624	>20	8.0	8.1	8.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.4	18.2	21.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	3	3
Boron	ppm	ASTM D5185m		4	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		5	4	3
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		65	74	43
Calcium	ppm	ASTM D5185m		2375	2468	2456
Phosphorus	ppm	ASTM D5185m		933	893	922
Zinc	ppm	ASTM D5185m		1096	1107	1129
Sulfur	ppm	ASTM D5185m		4279	4353	4437
Oxidation	Abs/.1mm	*ASTM D7414	>25	11.0	10.2	11.9
Base Number (BN)	mg KOH/g	ASTM D2896		6.8	6.5	6.7
Visc @ 100°C	cSt	ASTM D445		13.4	13.8	13.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DC0032173
Lab Number : 06146451
Unique Number : 10976529
Test Package : MOB 1 (Additional Tests: TBN)

THOMAS BENNETT & HUNTER INC
 70 JOHN ST
 WESTMINSTER, MD
 US 21157
 Contact: JOE STEPHAN
 jstephan@tbhconcrete.com
 T: (410)848-9030
 F: (410)848-9032

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)