



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
JOHN F SECREST
Machine Id
[JOHN F SECREST] 003 565425-3
Component
Starboard Main Engine
Fluid
CHEVRON DELO 710 LS (250 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0065923	MW0065916	MW0065937
Sample Date		Client Info		01 Apr 2024	01 Mar 2024	01 Feb 2024
Machine Age	hrs	Client Info		13093	12350	11654
Oil Age	hrs	Client Info		13093	12350	11654
Filter Age	hrs	Client Info		13093	83	0
Oil Changed		Client Info		N/A	Not Changd	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	20	14	13
Chromium	ppm	ASTM D5185m	>8	4	2	2
Nickel	ppm	ASTM D5185m	>2	1	0	0
Titanium	ppm	ASTM D5185m	>3	<1	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	4	1	2
Lead	ppm	ASTM D5185m	>18	8	5	6
Copper	ppm	ASTM D5185m	>80	24	14	16
Tin	ppm	ASTM D5185m	>14	11	6	7
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>20	7	4	5
Potassium	ppm	ASTM D5185m	>20	3	0	<1
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.5	0.5	0.5
Nitration	Abs/cm	*ASTM D7624	>20	8.3	8.2	8.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.0	17.1	16.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	3	1	1
Boron	ppm	ASTM D5185m		62	38	38
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		67	46	45
Manganese	ppm	ASTM D5185m		3	1	2
Magnesium	ppm	ASTM D5185m		20	17	18
Calcium	ppm	ASTM D5185m		4914	3675	3371
Phosphorus	ppm	ASTM D5185m		21	9	9
Zinc	ppm	ASTM D5185m		17	5	8
Sulfur	ppm	ASTM D5185m		3488	2600	2333
Oxidation	Abs/.1mm	*ASTM D7414	>25	8.9	8.9	8.9
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	8.91	9.28	9.26
Visc @ 100°C	cSt	ASTM D445	15.5	14.6	14.6	14.5


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0065923
Lab Number : 06146707
Unique Number : 10976785
Test Package : MAR 2
Received : 11 Apr 2024
Tested : 15 Apr 2024
Diagnosed : 15 Apr 2024 - Sean Felton

INGRAM BARGE
 900 S 3RD ST
 PADUCAH, KY
 US 42003

Contact: ANTHONY VAN CURA
 anthony.vancura@ingrambarga.com
 T: (270)415-4467
 F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)