



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
GALE C
Machine Id
[GALE C] 002 550006-2
Component
Center Main Engine
Fluid
CHEVRON DELO 710 LE (225 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0063211	MW0063263	MW0065710
Sample Date		Client Info		01 Apr 2024	14 Mar 2024	01 Feb 2024
Machine Age	hrs	Client Info		13330	12912	11893
Oil Age	hrs	Client Info		348	0	0
Filter Age	hrs	Client Info		0	0	292
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	10	10	11
Chromium	ppm	ASTM D5185m	>8	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	<1
Titanium	ppm	ASTM D5185m	>3	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	2	1	2
Lead	ppm	ASTM D5185m	>18	6	4	9
Copper	ppm	ASTM D5185m	>80	9	9	10
Tin	ppm	ASTM D5185m	>14	4	3	6
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>20	5	7	16
Potassium	ppm	ASTM D5185m	>20	0	0	2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	8.1	7.9	8.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.0	16.0	16.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	29	46	127
Boron	ppm	ASTM D5185m		46	44	59
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		50	46	44
Manganese	ppm	ASTM D5185m		<1	<1	1
Magnesium	ppm	ASTM D5185m		14	37	14
Calcium	ppm	ASTM D5185m		4112	3626	3704
Phosphorus	ppm	ASTM D5185m		9	18	5
Zinc	ppm	ASTM D5185m	10	10	25	13
Sulfur	ppm	ASTM D5185m		3102	2683	2387
Oxidation	Abs/.1mm	*ASTM D7414	>25	8.8	8.8	8.8
Base Number (BN)	mg KOH/g	ASTM D2896	9.2	3.84	10.06	9.44
Visc @ 100°C	cSt	ASTM D445	15.5	15.1	14.9	14.9


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW0063211

Lab Number : 06146728

Unique Number : 10976806

Test Package : MAR 2

Received : 11 Apr 2024

Tested : 15 Apr 2024

Diagnosed : 15 Apr 2024 - Wes Davis

INGRAM BARGE

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: ALLEN WILLHELM

allen.willhelm@ingrambarge.com

T: (270)415-4467

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)