



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
VOLVO A30G 742603
Component
Diesel Engine
Fluid
CHEVRON 15W40 (10 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ML0000029	ML0000002	VCP422872
Sample Date		Client Info		08 Apr 2024	08 Apr 2024	02 May 2023
Machine Age	hrs	Client Info		3417	4012	3417
Oil Age	hrs	Client Info		500	4012	0
Filter Age	hrs	Client Info		500	4012	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>200	5	14	8
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	<1	9	<1
Titanium	ppm	ASTM D5185m		<1	3	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>30	1	3	2
Lead	ppm	ASTM D5185m	>40	1	1	0
Copper	ppm	ASTM D5185m	>20	1	▲ 23	<1
Tin	ppm	ASTM D5185m	>20	1	2	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>20	4	9	5
Potassium	ppm	ASTM D5185m	>20	2	2	2
Fuel		WC Method	>3.0	<1.0	<1.0	0.8
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.1	0.2	0.3
Nitration	Abs/cm	*ASTM D7624	>20	6.4	7.9	7.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	16.7	21.8	20.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>50	0	2	3
Boron	ppm	ASTM D5185m		64	417	267
Barium	ppm	ASTM D5185m		0	<1	0
Molybdenum	ppm	ASTM D5185m		20	85	116
Manganese	ppm	ASTM D5185m		<1	2	<1
Magnesium	ppm	ASTM D5185m		100	365	605
Calcium	ppm	ASTM D5185m		2111	1416	1669
Phosphorus	ppm	ASTM D5185m		894	1061	786
Zinc	ppm	ASTM D5185m		968	1141	989
Sulfur	ppm	ASTM D5185m		3357	3303	2909
Oxidation	Abs/.1mm	*ASTM D7414	>25	10.1	15.3	15.7
Base Number (BN)	mg KOH/g	ASTM D2896		7.3	6.7	6.7
Visc @ 100°C	cSt	ASTM D445	14.4	12.6	12.3	12.3


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : ML0000029 **Received** : 12 Apr 2024
Lab Number : 06146898 **Tested** : 15 Apr 2024
Unique Number : 10976976 **Diagnosed** : 15 Apr 2024 - Sean Felton
Test Package : CONST (Additional Tests: TBN)

PLEASANT EXCAVATING COMPANY INC
 24024 FREDERICK ROAD
 CLARKSBURG, MD
 US 20871
 Contact: H TRENT
 HTRENT@PLEASANTS.ORG
 T: (301)252-5635
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)