

Machine Id **60510** Component **Diesel Engine** Fluid **DURAMAX 15W40 (--- GAL)**

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		DC0032945	DC0032863	DC0031507
Resample at the next service interval to monitor. Please specify the component make and model with your next sample.	Sample Date		Client Info		18 Mar 2024	26 Dec 2023	18 Sep 2023
	Machine Age	hrs	Client Info		12930	12609	12262
	Oil Age	hrs	Client Info		300	250	250
	Filter Age	hrs	Client Info		300	250	250
	Oil Changed		Client Info		Changed	Changed	Changed
	Filter Changed		Client Info		Changed	Changed	Changed
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR	Iron	ppm	ASTM D5185m	>100	4	5	4
	Chromium	ppm	ASTM D5185m		0	0	0
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0	0	0
	Titanium	ppm	ASTM D5185m		0	<1	0
	Silver	ppm	ASTM D5185m	>3	0	0	0
	Aluminum	ppm	ASTM D5185m	>20	1	1	2
	Lead	ppm	ASTM D5185m	>40	0	<1	0
	Copper	ppm	ASTM D5185m	>330	2	<1	<1
	Tin	ppm	ASTM D5185m	>15	<1	<1	0
	Vanadium	ppm	ASTM D5185m		0	<1	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	4	4	4
	Potassium	ppm	ASTM D5185m		<1	2	2
There is no indication of any contamination in the oil.	Fuel	le le	WC Method		<1.0	<1.0	<1.0
	Water		WC Method	>0.2	NEG	NEG	NEG
	Glycol		WC Method		NEG	NEG	NEG
	Soot %	%	*ASTM D7844	>3	0.4	0.4	0.3
	Nitration	Abs/cm	*ASTM D7624	>20	6.8	7.0	6.5
	Sulfation	Abs/.1mm	*ASTM D7415	>30	16.9	16.9	16.1
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1	<1	<1
	Boron	ppm	ASTM D5185m		3	3	<1
The BN result indicates that there is suitable alkalinity remaining in the	Barium	ppm	ASTM D5185m		0	0	0
oil. The condition of the oil is suitable for further service.	Molybdenum	ppm	ASTM D5185m		3	4	3
	Manganese	ppm	ASTM D5185m		<1	0	0
	Magnesium	ppm	ASTM D5185m		47	62	36
	Calcium	ppm	ASTM D5185m		2242	2064	2130
	Phosphorus	ppm	ASTM D5185m		895	895	827
	Zinc	ppm	ASTM D5185m		1042	1062	1008
	Sulfur	ppm	ASTM D5185m		4161	3582	4043
	Oxidation	Abs/.1mm	*ASTM D7414	>25	9.5	9.7	9.2
	Dese Number (DND		AOTA DOOOO		7.0	0.5	

Base Number (BN) mg KOH/g ASTM D2896

ASTM D445

Visc @ 100°C cSt

6.5

12.6

7.1

12.9

7.0

12.9


NORMAL


NORMAL

NORMAL

WEAR

CONTAMINATION FLUID CONDITION





FRANCIS O DAY 14900 SOUTHLAWN LN ROCKVILLE, MD US 20850

Sep18/23

en18/73

en18/73

Mar18/24

ar18/7

)ec26/23



 Unique Number
 : 10977137
 Diagnosed
 : 15 Apr 2024 - Wes Davis

 Certificate L2367
 Test Package
 : MOB 1 (Additional Tests: TBN)
 Cont

 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received

Tested

: 12 Apr 2024

: 15 Apr 2024

Contact: JAMIE FORESTER

T: F:

Laboratory

Sample No.

Lab Number : 06147059

: DC0032945

Contact/Location: JAMIE FORESTER - FRAROCDC Page 2 of 2