



# OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area  
**CLI TRANSPORT LP - MANASSAS**  
 Machine Id  
**VOLVO 8586 (S/N 4V4NC9EHXNN603553)**  
 Component  
**Diesel Engine**  
 Fluid  
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

## RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>NL0001842</b>	NL0001738	NL0001614
Sample Date		Client Info		<b>06 Feb 2024</b>	08 Aug 2023	21 May 2023
Machine Age	mls	Client Info		<b>558991</b>	522590	484871
Oil Age	mls	Client Info		<b>45000</b>	45000	45000
Filter Age	mls	Client Info		<b>45000</b>	45000	45000
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

## WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	<b>69</b>	91	56
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	<1	<1
Nickel	ppm	ASTM D5185m	>2	<b>0</b>	<1	0
Titanium	ppm	ASTM D5185m		<b>0</b>	0	0
Silver	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>25	<b>7</b>	9	4
Lead	ppm	ASTM D5185m	>40	<b>&lt;1</b>	0	0
Copper	ppm	ASTM D5185m	>330	<b>13</b>	5	2
Tin	ppm	ASTM D5185m	>15	<b>1</b>	0	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

## CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	<b>10</b>	6	4
Potassium	ppm	ASTM D5185m	>20	<b>1</b>	0	0
Fuel		WC Method	>6.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>3	<b>0.5</b>	0.6	0.4
Nitration	Abs/cm	*ASTM D7624	>20	<b>10.2</b>	9.4	8.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>21.7</b>	21.3	19.1
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

## FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>2</b>	0	0
Boron	ppm	ASTM D5185m	0	<b>6</b>	0	<1
Barium	ppm	ASTM D5185m	0	<b>&lt;1</b>	0	0
Molybdenum	ppm	ASTM D5185m	60	<b>66</b>	62	65
Manganese	ppm	ASTM D5185m	0	<b>1</b>	0	0
Magnesium	ppm	ASTM D5185m	1010	<b>953</b>	1025	1143
Calcium	ppm	ASTM D5185m	1070	<b>1152</b>	1144	1274
Phosphorus	ppm	ASTM D5185m	1150	<b>1032</b>	1042	1225
Zinc	ppm	ASTM D5185m	1270	<b>1284</b>	1423	1615
Sulfur	ppm	ASTM D5185m	2060	<b>3320</b>	3896	4590
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>17.4</b>	16.8	15.2
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>6.3</b>	6.1	7.8
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.6</b>	13.6	13.9


**FT-IR (Direct Trend)**




**Ferrous Alloys**




**Base Number**




**Viscosity @ 100°C**




**Non-ferrous Metals**



**Viscosity @ 100°C**



**Base Number**



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : NL0001842  
**Lab Number** : 06147108  
**Unique Number** : 10977186  
**Test Package** : FLEET

**Received** : 12 Apr 2024  
**Tested** : 15 Apr 2024  
**Diagnosed** : 15 Apr 2024 - Wes Davis

**FOX & JAMES NATIONALEASE - Manassas**  
 1145 INDUSTRIAL RD  
 MANASSAS, VA  
 US 20109  
 Contact: JOSH ROLAND  
 j.roland@foxandjames.com  
 T: (571)379-5296  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)