



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
HITACHI 300LC 1FFDDP70HMF840728

Component
Left Final Drive

Fluid
GEAR OIL SAE 80W90 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0206118	JR0178872	JR0171839
Sample Date		Client Info		10 Apr 2024	03 Oct 2023	19 Jun 2023
Machine Age	hrs	Client Info		3009	2513	2015
Oil Age	hrs	Client Info		2511	498	1436
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184		94	53	95
Iron	ppm	ASTM D5185m	>500	379	319	259
Chromium	ppm	ASTM D5185m	>10	5	4	5
Nickel	ppm	ASTM D5185m	>10	0	2	<1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	<1	0	3
Lead	ppm	ASTM D5185m	>25	0	<1	0
Copper	ppm	ASTM D5185m	>50	4	<1	1
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>75	9	9	9
Potassium	ppm	ASTM D5185m	>20	4	8	14
Water		WC Method	>0.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	LIGHT	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION


The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>170	2	0	3
Boron	ppm	ASTM D5185m	400	8	11	55
Barium	ppm	ASTM D5185m	200	1	0	0
Molybdenum	ppm	ASTM D5185m	12	<1	0	2
Manganese	ppm	ASTM D5185m		4	4	5
Magnesium	ppm	ASTM D5185m	12	1	<1	8
Calcium	ppm	ASTM D5185m	150	45	4	28
Phosphorus	ppm	ASTM D5185m	1650	437	425	506
Zinc	ppm	ASTM D5185m	125	20	18	28
Sulfur	ppm	ASTM D5185m	22500	22127	19198	16930
Visc @ 40°C	cSt	ASTM D445	143	144	146	185


Viscosity @ 40°C




PQ




Ferrous Alloys




Non-ferrous Metals



PQ



Viscosity @ 40°C



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0206118 **Received** : 12 Apr 2024
Lab Number : 06147646 **Tested** : 15 Apr 2024
Unique Number : 10977724 **Diagnosed** : 15 Apr 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

JRE - CHARLOTTE
 9550 STATESVILLE ROAD
 CHARLOTTE, NC
 US 28269
 Contact: CHARLOTTE SHOP
 myoung@jamesriverequipment.com
 T: (704)597-0211
 F: (704)596-6198

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)