



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
AARON F BARRETT
Machine Id
[AARON F BARRETT] 008 664964-8
Component
Starboard Genset
Fluid
CHEVRON DELO 400 LE 15W40 (5 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0062761	MW0062771	MW0055587
Sample Date		Client Info		01 Apr 2024	01 Feb 2024	27 Nov 2023
Machine Age	hrs	Client Info		49906	49255	48661
Oil Age	hrs	Client Info		180	272	397
Filter Age	hrs	Client Info		180	272	397
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	5	5	7
Chromium	ppm	ASTM D5185m	>4	0	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>5	0	<1	0
Aluminum	ppm	ASTM D5185m	>12	2	2	3
Lead	ppm	ASTM D5185m	>17	<1	<1	<1
Copper	ppm	ASTM D5185m	>70	2	2	<1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	6	7	6
Potassium	ppm	ASTM D5185m	>20	0	1	0
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	7.0	6.9	7.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.0	22.7	23.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	0	1
Boron	ppm	ASTM D5185m		306	355	295
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		114	122	121
Manganese	ppm	ASTM D5185m		1	2	2
Magnesium	ppm	ASTM D5185m		613	638	648
Calcium	ppm	ASTM D5185m		1621	1575	1684
Phosphorus	ppm	ASTM D5185m	1200	650	709	716
Zinc	ppm	ASTM D5185m	1300	743	791	817
Sulfur	ppm	ASTM D5185m	3200	2579	2917	2555
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.2	16.8	17.7
Base Number (BN)	mg KOH/g	ASTM D2896	9.6	9.3	8.8	8.7
Visc @ 100°C	cSt	ASTM D445	15.7	13.1	13.1	13.2


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW0062761

Lab Number : 06147987

Unique Number : 10978065

Test Package : MAR 2

Received : 12 Apr 2024

Tested : 15 Apr 2024

Diagnosed : 15 Apr 2024 - Wes Davis

INGRAM BARGE

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: DALE MORIE

dale.morie@ingrambarga.com

T: (270)415-4467

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)