



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
913171
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0112990	GFL0108411	GFL0098419
Sample Date		Client Info		02 Apr 2024	17 Jan 2024	31 Oct 2023
Machine Age	hrs	Client Info		2397	1826	1203
Oil Age	hrs	Client Info		2397	1826	1203
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	10	18	18
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	1	<1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>3	0	<1	<1
Aluminum	ppm	ASTM D5185m	>20	0	1	1
Lead	ppm	ASTM D5185m	>40	0	0	<1
Copper	ppm	ASTM D5185m	>330	0	2	8
Tin	ppm	ASTM D5185m	>15	0	1	2
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	3	4	7
Potassium	ppm	ASTM D5185m	>20	0	3	1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	0.7	0.7
Nitration	Abs/cm	*ASTM D7624	>20	8.5	8.3	8.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.0	19.9	20.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	0	4
Boron	ppm	ASTM D5185m	0	2	2	7
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	58	63	65
Manganese	ppm	ASTM D5185m	0	0	<1	<1
Magnesium	ppm	ASTM D5185m	1010	929	977	1008
Calcium	ppm	ASTM D5185m	1070	1022	1064	1140
Phosphorus	ppm	ASTM D5185m	1150	1023	978	1065
Zinc	ppm	ASTM D5185m	1270	1175	1236	1293
Sulfur	ppm	ASTM D5185m	2060	3065	3003	2925
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.0	15.5	16.7
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.7	7.4	7.9
Visc @ 100°C	cSt	ASTM D445	15.4	13.9	13.9	13.6


FT-IR (Direct Trend)




Ferrous Alloys




Base Number




Non-ferrous Metals




Viscosity @ 100°C



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : GFL0112990
 Lab Number : 06148281
 Unique Number : 10978359
 Test Package : FLEET

Received : 15 Apr 2024
 Tested : 15 Apr 2024
 Diagnosed : 15 Apr 2024 - Wes Davis

GFL Environmental - 918 - Hartland HC

630 E Industrial Drive
 Hartland, WI
 US 53029

Contact: David McCall
 david.mccall@gflenv.com

T: (262)369-3069

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: