WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL

Machine Id

HYUNDAI HX300LR 26766

Component
Diesel Engine

ECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History
Resample at the next service interval to monitor.	Sample Number		Client Info		WC0846960		
	Sample Date		Client Info		05 Apr 2024		
	Machine Age	hrs	Client Info		797		
	Oil Age	hrs	Client Info		260		
	Filter Age	hrs	Client Info		260		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
EAR	Iron	ppm	ASTM D5185m	>100	5		
	Chromium	ppm	ASTM D5185m		1		
Metal levels are typical for a new component breaking in.	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m	7 7	<1		
	Silver	ppm	ASTM D5185m	\3	0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m	7.0	<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
					_		
ONTAMINATION	Silicon	ppm	ASTM D5185m		7		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		2		
	Fuel		WC Method		<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method	-	NEG		
	Soot %	%	*ASTM D7844		0.1		
	Nitration	Abs/cm	*ASTM D7624	>20	7.9		
	Sulfation	Abs/.1mm	*ASTM D7415		19.5		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
<u></u>	Emulsified Water	scalar	*Visual	>0.2	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		1		
The DNI was all indicates that there is suitable all all all all and in the	Boron	ppm	ASTM D5185m		5		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		69		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		1041		
	Calcium	ppm	ASTM D5185m		1169		
	Phosphorus	ppm	ASTM D5185m		1110		
	Zinc	ppm	ASTM D5185m		1335		
	Sulfur	ppm	ASTM D5185m		3373		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	15.9		
	Base Number (BN)	mg KOH/g	ASTM D2896		8.4		
	Visc @ 100°C	cSt	ASTM D445		13.1		







Report Id: RWSBEL [WUSCAR] 06148326 (Generated: 04/15/2024 21:49:20) Rev: 1

Laboratory Sample No.

Lab Number : 06148326 Unique Number : 10978404

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0846960 Received **Tested**

: 15 Apr 2024 Diagnosed

: 15 Apr 2024 : 15 Apr 2024 - Wes Davis

WASTE PRO RIVERSIDE LANDFILL 11266 HWY 23

BELLE CHASSE, LA US 70037 Contact: TIM SCHOTSCH

T: (504)444-2968

F: (504)656-7607

Test Package : CONST (Additional Tests: TBN) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. tschotsch@disposalexpress.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: TIM SCHOTSCH - RWSBEL