



LEAHY-WOLF
Lubricating specialists since 1946

OIL ANALYSIS REPORT

| | |
|-----------------|---------------|
| WEAR | NORMAL |
| CONTAMINATION | NORMAL |
| FLUID CONDITION | NORMAL |



Machine Id
MACK 4004
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

| Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|----------------|-----|-------------|-----------|--------------------|-------------|-------------|
| Sample Number | | Client Info | | LW0009000 | LW0008630 | LW0007877 |
| Sample Date | | Client Info | | 09 Apr 2024 | 27 Jan 2024 | 14 Sep 2023 |
| Machine Age | mls | Client Info | | 0 | 0 | 0 |
| Oil Age | mls | Client Info | | 0 | 0 | 0 |
| Filter Age | mls | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Filter Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |

WEAR

All component wear rates are normal.

| | | | | | | |
|--------------|--------|-------------|------|--------------|------|------|
| Iron | ppm | ASTM D5185m | >120 | 7 | 4 | 12 |
| Chromium | ppm | ASTM D5185m | >20 | <1 | <1 | <1 |
| Nickel | ppm | ASTM D5185m | >5 | <1 | <1 | 0 |
| Titanium | ppm | ASTM D5185m | >2 | <1 | <1 | <1 |
| Silver | ppm | ASTM D5185m | >2 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 2 | 2 | 2 |
| Lead | ppm | ASTM D5185m | >40 | 1 | <1 | <1 |
| Copper | ppm | ASTM D5185m | >330 | 1 | 1 | 1 |
| Tin | ppm | ASTM D5185m | >15 | <1 | <1 | <1 |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | <1 |
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |

CONTAMINATION












There is no indication of any contamination in the oil.

| | | | | | | |
|------------------|----------|-------------|-------|----------------|-------|-------|
| Silicon | ppm | ASTM D5185m | >25 | 6 | 2 | 5 |
| Potassium | ppm | ASTM D5185m | >20 | 3 | 3 | 2 |
| Fuel | | WC Method | >3.0 | <1.0 | <1.0 | <1.0 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| Soot % | % | *ASTM D7844 | >4 | 0.7 | 0.7 | 0.9 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 8.7 | 9.0 | 8.9 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 21.0 | 21.0 | 21.9 |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| | | | | | | |
|------------------|----------|-------------|------|--------------|------|------|
| Sodium | ppm | ASTM D5185m | >216 | 2 | 0 | 3 |
| Boron | ppm | ASTM D5185m | 250 | 2 | 2 | 3 |
| Barium | ppm | ASTM D5185m | 10 | 0 | <1 | 0 |
| Molybdenum | ppm | ASTM D5185m | 100 | 65 | 62 | 56 |
| Manganese | ppm | ASTM D5185m | | <1 | 0 | <1 |
| Magnesium | ppm | ASTM D5185m | 450 | 1001 | 928 | 1070 |
| Calcium | ppm | ASTM D5185m | 3000 | 1146 | 1044 | 1329 |
| Phosphorus | ppm | ASTM D5185m | 1150 | 1069 | 947 | 1072 |
| Zinc | ppm | ASTM D5185m | 1350 | 1261 | 1190 | 1399 |
| Sulfur | ppm | ASTM D5185m | 4250 | 2894 | 2519 | 3430 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 16.5 | 17.2 | 17.2 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 8.5 | 6.6 | 6.1 | 6.2 |
| Visc @ 100°C | cSt | ASTM D445 | 14.4 | 14.2 | 13.9 | 14.3 |



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LW0009000
Lab Number : 06148424
Unique Number : 10978502
Test Package : MOB 1 (Additional Tests: TBN)

Received : 15 Apr 2024
Tested : 16 Apr 2024
Diagnosed : 16 Apr 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

LRs - NILES
 33541 REUM RD
 NILES, MI
 US 49120

Contact: JOHN HUGHES
 johnh@michianarecyclinganddisposal.com
 T: (269)684-0900 X:124
 F: