



WEAR	<b>ABNORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**JOHN DEERE 7760 1N07760XEB0035374**

Component  
**Rear Left Final Drive**

Fluid  
**GEAR OIL SAE 80W140 (--- GAL)**

### RECOMMENDATION

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>JR0201503</b>	---	---
Sample Date		Client Info		<b>14 Apr 2024</b>	---	---
Machine Age	hrs	Client Info		<b>3799</b>	---	---
Oil Age	hrs	Client Info		<b>0</b>	---	---
Filter Age	hrs	Client Info		<b>0</b>	---	---
Oil Changed		Client Info		<b>N/A</b>	---	---
Filter Changed		Client Info		<b>N/A</b>	---	---
Sample Status				<b>ABNORMAL</b>	---	---

### WEAR

Bearing and/or bushing wear is indicated.

PQ		ASTM D8184	>1250	<b>145</b>	---	---
Iron	ppm	ASTM D5185m	>750	<b>427</b>	---	---
Chromium	ppm	ASTM D5185m	>9	<b>5</b>	---	---
Nickel	ppm	ASTM D5185m	>10	<b>1</b>	---	---
Titanium	ppm	ASTM D5185m		<b>1</b>	---	---
Silver	ppm	ASTM D5185m		<b>0</b>	---	---
Aluminum	ppm	ASTM D5185m	>40	<b>5</b>	---	---
Lead	ppm	ASTM D5185m	>15	<b>▲ 39</b>	---	---
Copper	ppm	ASTM D5185m	>40	<b>▲ 83</b>	---	---
Tin	ppm	ASTM D5185m	>10	<b>▲ 10</b>	---	---
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	---	---
White Metal	scalar	*Visual	NONE	<b>NONE</b>	---	---
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	---	---

### CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	<b>18</b>	---	---
Potassium	ppm	ASTM D5185m	>20	<b>14</b>	---	---
Water		WC Method	>0.075	<b>NEG</b>	---	---
Silt	scalar	*Visual	NONE	<b>NONE</b>	---	---
Debris	scalar	*Visual	NONE	<b>NONE</b>	---	---
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	---	---
Appearance	scalar	*Visual	NORML	<b>NORML</b>	---	---
Odor	scalar	*Visual	NORML	<b>NORML</b>	---	---
Emulsified Water	scalar	*Visual	>0.075	<b>NEG</b>	---	---

### FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	<b>7</b>	---	---
Boron	ppm	ASTM D5185m	400	<b>179</b>	---	---
Barium	ppm	ASTM D5185m	200	<b>2</b>	---	---
Molybdenum	ppm	ASTM D5185m	12	<b>2</b>	---	---
Manganese	ppm	ASTM D5185m		<b>10</b>	---	---
Magnesium	ppm	ASTM D5185m	12	<b>9</b>	---	---
Calcium	ppm	ASTM D5185m	150	<b>115</b>	---	---
Phosphorus	ppm	ASTM D5185m	1650	<b>982</b>	---	---
Zinc	ppm	ASTM D5185m	125	<b>75</b>	---	---
Sulfur	ppm	ASTM D5185m	22500	<b>27151</b>	---	---
Visc @ 40°C	cSt	ASTM D445	263	<b>285</b>	---	---



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : JR0201503  
**Lab Number** : 06148972  
**Unique Number** : 10979050  
**Test Package** : CONST ( Additional Tests: PQ )

**Received** : 15 Apr 2024  
**Tested** : 16 Apr 2024  
**Diagnosed** : 17 Apr 2024 - Sean Felton

**JRE - WAKEFIELD**  
 10489 GENERAL MAHONE HWY  
 WAKEFIELD, VA  
 US 23888  
 Contact: BILL ACKER  
 backer@jamesriverequipment.com  
 T: (757)899-3232  
 F: (757)899-6464

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)