

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL



Machine Id **BELL B30E B93A631ET03010079**

Center Right Final Drive

GEAR OIL SAE 80W90 (--- GAL)

| GEAR OIL SAE 80W90 (GAL) | | | | | | | |
|---|------------------|--------|-------------|-----------|-------------|-----------|--------------|
| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
| Resample at the next service interval to monitor. | Sample Number | | Client Info | | BE0009030 | | |
| | Sample Date | | Client Info | | 09 Apr 2024 | | |
| | Machine Age | hrs | Client Info | | 1992 | | |
| | Oil Age | hrs | Client Info | | 0 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Changed | | |
| | Filter Changed | | Client Info | | Changed | | |
| | Sample Status | | | | NORMAL | | |
| WEAR | PQ | | ASTM D8184 | >3000 | 71 | | |
| | Iron | ppm | ASTM D5185m | >HR:1= | 233 | | |
| All component wear rates are normal. | Chromium | ppm | ASTM D5185m | | 2 | | |
| | Nickel | ppm | ASTM D5185m | >10 | 2 | | |
| | Titanium | ppm | ASTM D5185m | | <1 | | |
| | Silver | ppm | ASTM D5185m | | 0 | | |
| | Aluminum | ppm | ASTM D5185m | >25 | 5 | | |
| | Lead | ppm | ASTM D5185m | >25 | <1 | | |
| | Copper | ppm | ASTM D5185m | >50 | 53 | | |
| | Tin | ppm | ASTM D5185m | >10 | 2 | | |
| | Vanadium | ppm | ASTM D5185m | | <1 | | |
| | White Metal | scalar | *Visual | NONE | HEAVY | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >201 | 14 | | |
| | Potassium | ppm | ASTM D5185m | | 3 | | |
| There is no indication of any contamination in the oil. | Water | | WC Method | >1.01 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >1.01 | NEG | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | >170 | 1 | | |
| The condition of the oil is acceptable for the time in service. | Boron | ppm | ASTM D5185m | 400 | 5 | | |
| solution of the acceptance for the time in solution | Barium | ppm | ASTM D5185m | 200 | 1 | | |
| | Molybdenum | ppm | ASTM D5185m | 12 | 3 | | |
| | Manganese | ppm | ASTM D5185m | | 5 | | |
| | Magnesium | ppm | ASTM D5185m | | 15 | | |
| | Calcium | ppm | ASTM D5185m | | 44 | | |
| | Phosphorus | ppm | ASTM D5185m | | 555 | | |
| | Zinc | ppm | ASTM D5185m | | 45 | | |
| | Sulfur | ppm | ASTM D5185m | | 19463 | | |
| Report Id: bened005 [WUSCAR] 06149002 (Generated: 04/18/2024 10:06:31) Rev: 1 | Visc @ 40°C | cSt | ASTM D445 | 143 | 147 | · Subr | mitted By: ? |





Laboratory Sample No.

Lab Number : 06149002 Unique Number : 10979080

: BE0009030 Test Package : MOBCE

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Apr 2024 **Tested**

: 16 Apr 2024 Diagnosed : 18 Apr 2024 - Jonathan Hester

National Equipment Dealers LLC NE 215 Woodside Drive

Lexington, NC US 27292

Contact: Steven Gawthrop sgawthrop@nedealers.com

T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: