

DOOSAN DX140LCR5 EX83 (S/N DHKCEBBSJG0001513)

Left Planetary

DURALENE Dura-Gear 80W90 (--- GAL)

| RECOMMENDATION |
|----------------|
|----------------|

Resample at the next service interval to monitor.

WEAR

All component wear rates are normal.

CONTAMINATION


There is no indication of any contamination in the oil.


FLUID CONDITION


The condition of the oil is acceptable for the time in service.

| Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|--------------------------|---------------|--------------------------|------------|-------------|----------|----------|
| Sample Number | | Client Info | | DC0035455 | | |
| Sample Date | | Client Info | | 19 Mar 2024 | | |
| Machine Age | hrs | Client Info | | 4799 | | |
| Oil Age | hrs | Client Info | | 1000 | | |
| Filter Age | hrs | Client Info | | 0 | | |
| Oil Changed | | Client Info | | Changed | | |
| Filter Changed | | Client Info | | N/A | | |
| Sample Status | | | | NORMAL | | |
| Iron | | ASTM D5185m | >500 | 110 | | |
| Chromium | ppm ppm | ASTM D5185m | >10 | 1 | | |
| Nickel | | ASTM D5185m | >10 | ، <1 | | |
| Titanium | ppm | ASTM D5185m | >10 | <1 | | |
| Silver | ppm | ASTM D5185m | | 0 | | |
| Aluminum | ppm | ASTM D5185m | >25 | 3 | | |
| Lead | ppm | ASTM D5185m | >20 >25 | ა <1 | | |
| Copper | ppm | ASTM D5185m | >25 | <1 4 | | |
| Tin | ppm | ASTM D5185m | >75 >10 | 4 <1 | | |
| Vanadium | ppm | ASTM D5185m | >10 | <1 | | |
| White Metal | ppm scalar | *Visual | NONE | NONE | | |
| Yellow Metal | | | NONE | NONE | | |
| | scalar | *Visual | NONE | | | |
| Silicon | ppm | ASTM D5185m | >75 | 6 | | |
| Potassium | ppm | ASTM D5185m | >20 | 3 | | |
| Water | | WC Method | >0.2 | NEG | | |
| Silt | scalar | *Visual | NONE | NONE | | |
| Debris | scalar | *Visual | NONE | NONE | | |
| Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| Appearance | scalar | *Visual | NORML | NORML | | |
| Odor | scalar | *Visual | NORML | NORML | | |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| Q = d ¹ = set | | | | • | | |
| Sodium | ppm | ASTM D5185m | | 2 | | |
| Boron | ppm | ASTM D5185m | | 92 | | |
| Barium | ppm | ASTM D5185m | | 1 | | |
| Molybdenum | ppm | ASTM D5185m | | 2 | | |
| Manganese | ppm | ASTM D5185m | | 1 | | |
| Magnesium | ppm | ASTM D5185m | | 15 | | |
| Calcium | ppm | ASTM D5185m | | 873 | | |
| Phosphorus | ppm | ASTM D5185m | | 937 | | |
| Zinc | ppm | ASTM D5185m | | 447 | | |
| Sulfur | ppm cSt | ASTM D5185m ASTM D445 | | 18031 | | |
| Visc @ 40°C | | ALLEA DAAE | | 86.1 | | |

Contact/Location: JONATHAN KUENTZ - ROSMOU







Contact/Location: JONATHAN KUENTZ - ROSMOU

Page 2 of 2