

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL

Ascendum Machinery Machine Id VOLVO L90H 626964 Component Rear Axle Fluid VOLVO WB 102 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

WEAR

All component wear rates are normal.

CONTAMINATION


There is no indication of any contamination in the oil.


FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ASC0007082		
Sample Date		Client Info		10 Apr 2024		
Machine Age	hrs	Client Info		433		
Oil Age	hrs	Client Info		433		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		Not Changd		
Sample Status				NORMAL		
Iron	ppm	ASTM D5185m	>300	16		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m	~7	0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>15	<1		
Lead	ppm	ASTM D5185m	>4	<1		
Copper	ppm	ASTM D5185m	>200	14		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>75	15		
Potassium	ppm	ASTM D5185m	>20	2		
Water		WC Method	>0.2	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Sodium	ppm	ASTM D5185m		3		
Boron	ppm	ASTM D5185m		146		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		2		
Magnesium	ppm	ASTM D5185m		8		
Calcium	ppm	ASTM D5185m		3857		
Phosphorus	ppm	ASTM D5185m		1318		
Zinc	ppm	ASTM D5185m		1582		
Sulfur	ppm	ASTM D5185m		4737		
Visc @ 40°C	cSt	ASTM D445	55	41.5		

Submitted By: CLAYTON SMITH





IAA - INSURANCE AUTO AUCTIONS - OAK BROOK 701 HARGER RD, SUITE 201 OAK BROOK, IL US 60523 Contact: Service Manager



Unique Number : 10979228 Diagnosed : 16 Apr 2024 - Wes Davis Test Package : CONST Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received

Tested

: 15 Apr 2024

: 16 Apr 2024

T:

F:

Laboratory

Sample No.

Lab Number : 06149150

: ASC0007082

Submitted By: CLAYTON SMITH Page 2 of 2