WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL





Ascendum Machinery VOLVO L90H 626964


Transmission (Auto)


VOLVO AT 102 (--- GAL)

VOLVO AT 102 (GAL)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		ASC0007083		
riesample at the next service interval to monitor.	Sample Date		Client Info		10 Apr 2024		
	Machine Age	hrs	Client Info		433		
	Oil Age	hrs	Client Info		433		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>160	45		
	Chromium	ppm	ASTM D5185m		0		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	>5	0		
	Aluminum	ppm	ASTM D5185m	>50	0		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m	>225	3		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon		ASTM D5185m	. 00	7		
	Potassium	ppm	ASTM D5185m		0		
There is no indication of any contamination in the fluid.	Water	ррш	WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		5		
	Boron	ppm	ASTM D5185m	187	69		
The condition of the fluid is acceptable for the time in service.	Barium	ppm	ASTM D5185m		2		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		5		
	Magnesium	ppm	ASTM D5185m		4		
	Calcium	ppm	ASTM D5185m	215	88		
	Phosphorus	ppm	ASTM D5185m	445	167		
	Zinc	ppm	ASTM D5185m	56	30		
	Sulfur	ppm	ASTM D5185m	1336	1667		
	Visc @ 40°C	cSt	ASTM D445	35.3	28.5		











Certificate L2367

Laboratory Sample No. Unique Number : 10979255

Lab Number : 06149177

Test Package : CONST

: ASC0007083

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Apr 2024 **Tested**

: 16 Apr 2024 Diagnosed : 16 Apr 2024 - Wes Davis

IAA - INSURANCE AUTO AUCTIONS - OAK BROOK 701 HARGER RD, SUITE 201 OAK BROOK, IL

US 60523 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: