

RECOMMENDATION

Current

History1

History2

Limit/Abn

Machine Id VOLVO A45G 752243

Transmission (Auto)

VOLVO AUTOMATIC TRANSMISSION FLUID AT102 (--- GAL)

Test

UOM

Method

| Resample at the next service interval to monitor. | Sample Number | | Client Info | | VCP436846 | |
|---|------------------|--------|-------------|-------|-------------|--|
| | Sample Date | | Client Info | | 10 Apr 2024 | |
| | Machine Age | hrs | Client Info | | 729 | |
| | Oil Age | hrs | Client Info | | 0 | |
| | Filter Age | hrs | Client Info | | 0 | |
| | Oil Changed | | Client Info | | Not Changd | |
| | Filter Changed | | Client Info | | Not Changd | |
| | Sample Status | | | | NORMAL | |
| WEAR | Iron | ppm | ASTM D5185m | >160 | 28 | |
| All component wear rates are normal. | Chromium | ppm | ASTM D5185m | >5 | 0 | |
| | Nickel | ppm | ASTM D5185m | | 2 | |
| | Titanium | ppm | ASTM D5185m | | 0 | |
| | Silver | ppm | ASTM D5185m | >5 | 0 | |
| | Aluminum | ppm | ASTM D5185m | >50 | 10 | |
| | Lead | ppm | ASTM D5185m | >50 | 0 | |
| | Copper | ppm | ASTM D5185m | >225 | 21 | |
| | Tin | ppm | ASTM D5185m | >10 | 0 | |
| | Vanadium | ppm | ASTM D5185m | | 0 | |
| | White Metal | scalar | *Visual | NONE | NONE | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >20 | 15 | |
| There is no indication of any contamination in the fluid. | Potassium | ppm | ASTM D5185m | | 0 | |
| | Water | 1-1- | WC Method | | NEG | |
| | Silt | scalar | *Visual | NONE | NONE | |
| | Debris | scalar | *Visual | NONE | NONE | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | |
| | Appearance | scalar | *Visual | NORML | NORML | |
| | Odor | scalar | *Visual | NORML | NORML | |
| | Emulsified Water | scalar | *Visual | >0.1 | NEG | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | | 6 | |
| The condition of the fluid is acceptable for the time in service. | Boron | ppm | ASTM D5185m | 187 | 74 | |
| | Barium | ppm | ASTM D5185m | | 0 | |
| | Molybdenum | ppm | ASTM D5185m | | 0 | |
| | Manganese | ppm | ASTM D5185m | | 3 | |
| | Magnesium | ppm | ASTM D5185m | | 0 | |
| | Calcium | ppm | ASTM D5185m | | 64 | |
| | Phosphorus | ppm | ASTM D5185m | | 165 | |
| | Zinc | ppm | ASTM D5185m | | 0 | |
| | Sulfur | ppm | ASTM D5185m | | 1785 | |
| | | 0 | | 05.0 | | |


Contact/Location: TODD LARK - VOLVO0090


29.3

ASTM D445 35.3

Visc @ 40°C

cSt





ALTA EQUIPMENT COMPANY Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 回流 Sample No. Received 5151 DR MARTIN LUTHER KING BLVD : VCP436846 : 15 Apr 2024 Lab Number : 06149208 FORT MYERS, FL Tested : 16 Apr 2024 Diagnosed Unique Number : 10979286 : 17 Apr 2024 - Sean Felton US 33905 Test Package : MOB 1 Contact: TODD LARK Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. tlark@altaequipfl.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (239)481-3302

Contact/Location: TODD LARK - VOLVO0090 Page 2 of 2