WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

JOHN DEERE 650P 1T0650PAVPLX05080

Right Final Drive

{not provided} (--- GAL)

not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		JR0206251	JR0206677	
	Sample Date		Client Info		11 Apr 2024	11 Apr 2024	
	Machine Age	hrs	Client Info		465	465	
	Oil Age	hrs	Client Info		465	465	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Not Changd	Not Changd	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	PQ		ASTM D8184		110	53	
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>500	126	70	
	Chromium	ppm	ASTM D5185m	>10	2	2	
	Nickel	ppm	ASTM D5185m	>10	<1	<1	
	Titanium	ppm	ASTM D5185m		<1	<1	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>25	12	3	
	Lead	ppm	ASTM D5185m	>25	0	<1	
	Copper	ppm	ASTM D5185m	>50	<1	1	
	Tin	ppm	ASTM D5185m	>10	<1	<1	
	Vanadium	ppm	ASTM D5185m		0	<1	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m		40	11	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		1	2	
	Water		WC Method	>0.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3	1	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		1	<1	
	Barium	ppm	ASTM D5185m		3	4	
	Molybdenum	ppm	ASTM D5185m		<1	1	
	Manganese	ppm	ASTM D5185m		4	4	
	Magnesium	ppm	ASTM D5185m		96	112	
	Calcium	ppm	ASTM D5185m		3185	3666	
	Phosphorus	ppm	ASTM D5185m		933	1119	
	Zinc	ppm	ASTM D5185m		1077	1327	
	Sulfur	ppm	ASTM D5185m		3794	3996	
	Visc @ 40°C	cSt	ASTM D445		52.6	52.5	





Report Id: JAMCHA [WUSCAR] 06149620 (Generated: 04/18/2024 11:56:09) Rev: 1

Laboratory Sample No.

: JR0206251 Lab Number : 06149620 Unique Number : 10979698

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Apr 2024 **Tested** : 16 Apr 2024

Diagnosed : 18 Apr 2024 - Sean Felton Test Package : CONST (Additional Tests: PQ)

JRE - CHARLOTTE 9550 STATESVILLE ROAD CHARLOTTE, NC

US 28269 Contact: CHARLOTTE SHOP

F: (704)596-6198

myoung@jamesriverequipment.com T: (704)597-0211

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)