



PacLease

# OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**857-4672**  
 Component  
**Diesel Engine**  
 Fluid  
**CHEVRON DELO 400 SAE 10W30 (--- GAL)**

## RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>RPL0014266</b>	RPL0010809	RPL0010709
Sample Date		Client Info		<b>14 Mar 2024</b>	15 Sep 2023	01 Feb 2023
Machine Age	hrs	Client Info		<b>9752</b>	8053	5659
Oil Age	hrs	Client Info		<b>0</b>	0	0
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>N/A</b>	Changed	Changed
Filter Changed		Client Info		<b>N/A</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	ABNORMAL	NORMAL

## WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	<b>24</b>	96	64
Chromium	ppm	ASTM D5185m	>20	<b>1</b>	3	2
Nickel	ppm	ASTM D5185m	>4	<b>&lt;1</b>	<1	0
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	0
Silver	ppm	ASTM D5185m	>3	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>6</b>	12	16
Lead	ppm	ASTM D5185m	>40	<b>3</b>	13	6
Copper	ppm	ASTM D5185m	>330	<b>1</b>	10	4
Tin	ppm	ASTM D5185m	>15	<b>1</b>	2	1
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

## CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>8</b>	13	10
Potassium	ppm	ASTM D5185m	>20	<b>10</b>	26	38
Fuel		WC Method	>5	<b>&lt;1.0</b>	<1.0	1.8
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>3	<b>0.6</b>	1.2	0.9
Nitration	Abs/cm	*ASTM D7624	>20	<b>13.0</b>	15.8	12.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>25.1</b>	34.4	29.2
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

## FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>5</b>	4	5
Boron	ppm	ASTM D5185m		<b>27</b>	20	20
Barium	ppm	ASTM D5185m		<b>1</b>	0	0
Molybdenum	ppm	ASTM D5185m		<b>44</b>	31	15
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	1	1
Magnesium	ppm	ASTM D5185m		<b>524</b>	639	676
Calcium	ppm	ASTM D5185m		<b>1743</b>	1535	1520
Phosphorus	ppm	ASTM D5185m	1260	<b>796</b>	721	747
Zinc	ppm	ASTM D5185m	1400	<b>947</b>	911	960
Sulfur	ppm	ASTM D5185m		<b>2689</b>	2657	3148
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>26.9</b>	37.8	25.0
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	<b>6.4</b>	▲ 2.8	4.6
Visc @ 100°C	cSt	ASTM D445	11.1	<b>11.7</b>	● 13.7	12.0



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : RPL0014266  
**Lab Number** : 06149780  
**Unique Number** : 10979858  
**Test Package** : FLEET

**RTL PACLEASE - 7001 - Houston**  
 6300 N. Loop East  
 Houston, TX  
 US 77026  
 Contact: RODNEY BRIGGS  
 briggsr@rushenterprises.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: