

Machine Id

VOLVO A30G 752450 Component Diesel Engine Fluid DIESEL ENGINE OIL SAE 15W40 (--- GAL)

Diesel Engine Oil SAE 15W40 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		ML0000620		
	Sample Date		Client Info		10 Apr 2024		
	Machine Age	hrs	Client Info		3499		
	Oil Age	hrs	Client Info		500		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>100	14		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	>2	0		
	Aluminum	ppm	ASTM D5185m	>25	4		
	Lead	ppm	ASTM D5185m	>40	<1		
	Copper	ppm	ASTM D5185m	>330	2		
	Tin	ppm	ASTM D5185m	>15	1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nom	ASTM D5185m	> 25	8		
CONTAMINATION	Potassium	ppm ppm	ASTM D5185m		2		
Fuel content negligible. There is no indication of any contamination in the oil.	Fuel	%	ASTM D310311		0.5		
	Water	70	WC Method		NEG		
	Glycol		WC Method	20.L	NEG		
	Soot %	%	*ASTM D7844	>3	0.2		
	Nitration	Abs/cm	*ASTM D7624		7.0		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	21.7		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Sodium	ppm	ASTM D5185m	>158	1		
	Boron	ppm	ASTM D5185m	250	65		
	Barium	ppm	ASTM D5185m	10	<1		
	Molybdenum	ppm	ASTM D5185m	100	47		
	Manganese	ppm	ASTM D5185m		1		
	Magnesium	ppm	ASTM D5185m		514		
	Calcium	ppm	ASTM D5185m		1746		
	Phosphorus	ppm	ASTM D5185m		825		
	Zinc	ppm	ASTM D5185m		939		
	Sulfur	ppm	ASTM D5185m		2934		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	20.2		


Base Number (BN) mg KOH/g ASTM D2896 8.5

ASTM D445 14.4

Visc @ 100°C cSt

9.7

12.4



WILLIAM HAZEL Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : ML0000620 Received PO BOX 600 : 16 Apr 2024 Lab Number : 06149833 Tested CHANTILLY, VA : 22 Apr 2024 Unique Number : 10979911 Diagnosed : 22 Apr 2024 - Jonathan Hester US 20153 Test Package : CONST (Additional Tests: FuelDilution, PercentFuel, TBN) Contact: SERVICE MANAGER Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (703)378-8300 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F:

Submitted By: Service - Alex Anderson Page 2 of 2