



PacLease

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
857-5119
 Component
Diesel Engine
 Fluid
CHEVRON DELO 400 SAE 10W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RPL0014493	RPL0014051	---
Sample Date		Client Info		04 Apr 2024	09 Dec 2023	---
Machine Age	hrs	Client Info		1473	959	---
Oil Age	hrs	Client Info		0	0	---
Filter Age	hrs	Client Info		0	0	---
Oil Changed		Client Info		Changed	Changed	---
Filter Changed		Client Info		Changed	Changed	---
Sample Status				NORMAL	NORMAL	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	30	86	---
Chromium	ppm	ASTM D5185m	>20	2	4	---
Nickel	ppm	ASTM D5185m	>4	<1	0	---
Titanium	ppm	ASTM D5185m		<1	0	---
Silver	ppm	ASTM D5185m	>3	<1	0	---
Aluminum	ppm	ASTM D5185m	>20	29	67	---
Lead	ppm	ASTM D5185m	>40	3	6	---
Copper	ppm	ASTM D5185m	>330	6	36	---
Tin	ppm	ASTM D5185m	>15	3	4	---
Vanadium	ppm	ASTM D5185m		<1	0	---
White Metal	scalar	*Visual	NONE	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	---

CONTAMINATION









Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	14	52	---
Potassium	ppm	ASTM D5185m	>20	75	203	---
Fuel		WC Method	>5	<1.0	<1.0	---
Water		WC Method	>0.2	NEG	NEG	---
Glycol		WC Method		NEG	NEG	---
Soot %	%	*ASTM D7844	>3	0.6	0.7	---
Nitration	Abs/cm	*ASTM D7624	>20	9.4	11.8	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.4	24.7	---
Silt	scalar	*Visual	NONE	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	6	---
Boron	ppm	ASTM D5185m		38	21	---
Barium	ppm	ASTM D5185m		2	0	---
Molybdenum	ppm	ASTM D5185m		44	13	---
Manganese	ppm	ASTM D5185m		2	6	---
Magnesium	ppm	ASTM D5185m		527	774	---
Calcium	ppm	ASTM D5185m		1636	1358	---
Phosphorus	ppm	ASTM D5185m	1260	788	765	---
Zinc	ppm	ASTM D5185m	1400	918	857	---
Sulfur	ppm	ASTM D5185m		2756	2832	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	23.6	22.4	---
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	8.1	5.2	---
Visc @ 100°C	cSt	ASTM D445	11.1	10.6	11.3	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RPL0014493
Lab Number : 06149842
Unique Number : 10979920
Test Package : FLEET

RTL PACLEASE - 7001 - Houston
 6300 N. Loop East
 Houston, TX
 US 77026

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact: RODNEY BRIGGS
 briggsr@rushenterprises.com
 T:
 F: