



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
3987
 Component
Diesel Engine
 Fluid
CHEVRON DELO 400 XLE 10W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0896018	WC0833244	WC0833144
Sample Date		Client Info		28 Mar 2024	28 Dec 2023	28 Jun 2023
Machine Age	mls	Client Info		161002	116658	41957
Oil Age	mls	Client Info		44500	37443	41957
Filter Age	mls	Client Info		44500	37443	41957
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	30	6	58
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>4	<1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	<1	0	<1
Aluminum	ppm	ASTM D5185m	>20	10	4	33
Lead	ppm	ASTM D5185m	>40	<1	0	<1
Copper	ppm	ASTM D5185m	>330	3	<1	19
Tin	ppm	ASTM D5185m	>15	1	0	2
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	14	5	11
Potassium	ppm	ASTM D5185m	>20	13	9	71
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.9	0.3	0.6
Nitration	Abs/cm	*ASTM D7624	>20	10.9	9.8	10.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	26.7	20.5	25.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	2	5
Boron	ppm	ASTM D5185m		23	29	29
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		5	1	6
Manganese	ppm	ASTM D5185m		1	0	3
Magnesium	ppm	ASTM D5185m		798	706	829
Calcium	ppm	ASTM D5185m	2900	1439	1256	1521
Phosphorus	ppm	ASTM D5185m	1100	807	655	745
Zinc	ppm	ASTM D5185m	1200	891	828	1004
Sulfur	ppm	ASTM D5185m	4000	3352	2802	3465
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.0	15.7	20.5
Base Number (BN)	mg KOH/g	ASTM D2896	10.3	5.1	6.2	5.7
Visc @ 100°C	cSt	ASTM D445	11.9	11.9	13.4	12.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0896018
Lab Number : 06149846
Unique Number : 10979924
Test Package : FLEET

Received : 16 Apr 2024
Tested : 17 Apr 2024
Diagnosed : 17 Apr 2024 - Wes Davis

LTI/MILKY WAY - MOSES
 120 WISER LANE
 MOSES LAKE, WA
 US 98837

Contact: MIGUEL PEREZ
 mperez@lynden.com; dougb@wearcheckusa.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (509)765-5840
 F: (509)765-5636