



WEAR CHECK

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
3986
 Component
Diesel Engine
 Fluid
CHEVRON DELO 400 XLE 10W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0896020	WC0833246	WC0833184
Sample Date		Client Info		04 Mar 2024	06 Dec 2023	24 Aug 2023
Machine Age	mls	Client Info		170583	132743	81049
Oil Age	mls	Client Info		37929	51698	38933
Filter Age	mls	Client Info		37929	51698	38933
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	27	27	29
Chromium	ppm	ASTM D5185m	>20	<1	0	0
Nickel	ppm	ASTM D5185m	>4	4	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	14	17	11
Lead	ppm	ASTM D5185m	>40	<1	<1	0
Copper	ppm	ASTM D5185m	>330	10	6	5
Tin	ppm	ASTM D5185m	>15	1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	12	11	8
Potassium	ppm	ASTM D5185m	>20	22	32	25
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.9	0.9	0.7
Nitration	Abs/cm	*ASTM D7624	>20	11.3	11.4	10.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	26.1	26.5	26.3
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	3	4
Boron	ppm	ASTM D5185m		16	13	15
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		2	<1	<1
Manganese	ppm	ASTM D5185m		1	0	<1
Magnesium	ppm	ASTM D5185m		787	781	799
Calcium	ppm	ASTM D5185m	2900	1400	1369	1502
Phosphorus	ppm	ASTM D5185m	1100	768	704	728
Zinc	ppm	ASTM D5185m	1200	890	895	853
Sulfur	ppm	ASTM D5185m	4000	3240	2829	3358
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.7	21.3	21.4
Base Number (BN)	mg KOH/g	ASTM D2896	10.3	5.5	5.2	4.7
Visc @ 100°C	cSt	ASTM D445	11.9	11.8	12.0	11.9



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0896020
Lab Number : 06149852
Unique Number : 10979930
Test Package : FLEET

LTI/MILKY WAY - MOSES
 120 WISER LANE
 MOSES LAKE, WA
 US 98837

Contact: MIGUEL PEREZ
 mperez@lynden.com; dougb@wearcheckusa.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (509)765-5840
 F: (500)765-5636