



PacLease

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
857-4873
 Component
Diesel Engine
 Fluid
CHEVRON DELO 400 SAE 10W30 (--- GAL)

RECOMMENDATION

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RPL0014279	RPL0014639	RPL0010610
Sample Date		Client Info		06 Mar 2024	14 Nov 2023	16 Mar 2023
Machine Age	hrs	Client Info		1585	14606	8884
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	Not Changd	Not Changd
Filter Changed		Client Info		N/A	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	41	17	50
Chromium	ppm	ASTM D5185m	>20	2	<1	2
Nickel	ppm	ASTM D5185m	>4	<1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	<1	<1	0
Aluminum	ppm	ASTM D5185m	>20	25	6	32
Lead	ppm	ASTM D5185m	>40	2	0	2
Copper	ppm	ASTM D5185m	>330	7	4	34
Tin	ppm	ASTM D5185m	>15	2	0	2
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. No other contaminants were detected in the oil.

Silicon	ppm	ASTM D5185m	>25	17	10	45
Potassium	ppm	ASTM D5185m	>20	80	22	96
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.2	0.3
Nitration	Abs/cm	*ASTM D7624	>20	8.9	6.3	9.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8	21.2	19.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		4	2	4
Boron	ppm	ASTM D5185m		58	56	66
Barium	ppm	ASTM D5185m		2	3	0
Molybdenum	ppm	ASTM D5185m		52	38	16
Manganese	ppm	ASTM D5185m		2	0	6
Magnesium	ppm	ASTM D5185m		703	486	658
Calcium	ppm	ASTM D5185m		2171	1572	1292
Phosphorus	ppm	ASTM D5185m	1260	1088	671	688
Zinc	ppm	ASTM D5185m	1400	1211	854	825
Sulfur	ppm	ASTM D5185m		3734	2741	2867
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.0	19.0	15.3
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	9.2	9.6	6.9
Visc @ 100°C	cSt	ASTM D445	11.1	10.9	10.9	11.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RPL0014279
Lab Number : 06149928
Unique Number : 10980006
Test Package : FLEET

RTL PACLEASE - 7001 - Houston
 6300 N. Loop East
 Houston, TX
 US 77026
 Contact: RODNEY BRIGGS
 briggs@rushenterprises.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: