



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 748L 1DW748LBHNF713628
 Component
Diesel Engine
 Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (28 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0208800	JR0200645	JR0194022
Sample Date		Client Info		14 Apr 2024	06 Feb 2024	14 Dec 2023
Machine Age	hrs	Client Info		5533	5082	4761
Oil Age	hrs	Client Info		451	321	771
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	SEVERE	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	7	43	14
Chromium	ppm	ASTM D5185m	>11	<1	2	<1
Nickel	ppm	ASTM D5185m	>5	1	1	2
Titanium	ppm	ASTM D5185m		0	1	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>31	2	42	3
Lead	ppm	ASTM D5185m	>26	0	2	<1
Copper	ppm	ASTM D5185m	>26	3	28	2
Tin	ppm	ASTM D5185m	>4	1	<1	<1
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	5	60	9
Potassium	ppm	ASTM D5185m	>20	<1	12	5
Fuel	%	ASTM D3524	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.4	0.6
Nitration	Abs/cm	*ASTM D7624	>20	8.8	8.5	9.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.7	21.5	25.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	3	2	1
Boron	ppm	ASTM D5185m		133	212	47
Barium	ppm	ASTM D5185m		0	0	13
Molybdenum	ppm	ASTM D5185m		166	249	215
Manganese	ppm	ASTM D5185m		<1	1	<1
Magnesium	ppm	ASTM D5185m		627	793	665
Calcium	ppm	ASTM D5185m		1653	1275	1575
Phosphorus	ppm	ASTM D5185m		827	896	897
Zinc	ppm	ASTM D5185m		1009	1054	1108
Sulfur	ppm	ASTM D5185m		3297	2889	3065
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.7	15.6	19.5
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.1	8.3	6.5
Visc @ 100°C	cSt	ASTM D445	15.4	12.9	13.5	13.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0208800 **Received** : 16 Apr 2024
Lab Number : 06150184 **Tested** : 17 Apr 2024
Unique Number : 10980262 **Diagnosed** : 18 Apr 2024 - Don Baldrige
Test Package : CONST (Additional Tests: FuelDilution, TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - GREENVILLE
 3604 HIGHWAY 264 E
 GREENVILLE, NC
 US 27834-5800

Contact: GREENVILLE SHOP
 christopher.martin@jamesriverequipment.com

T:
 F: