



# OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area  
**Store 2 - Beaver [149850]**  
Machine Id  
**JOHN DEERE 250P 1FF250PAPPF000060**  
Component  
**Hydraulic System**  
Fluid  
**HITACHI HYDRAULIC SUPER EX 46HN (39 GAL)**

## RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>LEC0048087</b>	LEC0046553	LEC0042219
Sample Date		Client Info		<b>12 Apr 2024</b>	05 Feb 2024	26 Oct 2023
Machine Age	hrs	Client Info		<b>350</b>	324	110
Oil Age	hrs	Client Info		<b>350</b>	324	110
Filter Age	hrs	Client Info		<b>350</b>	324	110
Oil Changed		Client Info		<b>Not Chngd</b>	Not Chngd	Not Chngd
Filter Changed		Client Info		<b>Not Chngd</b>	Not Chngd	Not Chngd
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

## WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	<b>15</b>	12	12
Iron	ppm	ASTM D5185m	>32	<b>1</b>	0	1
Chromium	ppm	ASTM D5185m	>9	<b>0</b>	0	0
Nickel	ppm	ASTM D5185m	>5	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m		<b>0</b>	0	<1
Silver	ppm	ASTM D5185m		<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>9	<b>0</b>	0	1
Lead	ppm	ASTM D5185m	>28	<b>0</b>	0	<1
Copper	ppm	ASTM D5185m	>50	<b>2</b>	3	1
Tin	ppm	ASTM D5185m	>5	<b>&lt;1</b>	<1	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

## CONTAMINATION











The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>11	<b>&lt;1</b>	0	<1
Potassium	ppm	ASTM D5185m	>20	<b>1</b>	0	2
Water		WC Method	>0.075	<b>NEG</b>	NEG	NEG
Particles >4µm		ASTM D7647	>80000	<b>3634</b>	4463	4244
Particles >6µm		ASTM D7647	>20000	<b>268</b>	236	363
Particles >14µm		ASTM D7647	>640	<b>19</b>	10	23
Particles >21µm		ASTM D7647	>160	<b>7</b>	2	7
Particles >38µm		ASTM D7647	>40	<b>1</b>	0	1
Particles >71µm		ASTM D7647	>10	<b>0</b>	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	<b>19/15/11</b>	19/15/10	19/16/12
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	<b>NEG</b>	NEG	NEG

## FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	<b>1</b>	<1	0
Boron	ppm	ASTM D5185m		<b>0</b>	4	0
Barium	ppm	ASTM D5185m		<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m		<b>0</b>	<1	<1
Manganese	ppm	ASTM D5185m		<b>0</b>	0	0
Magnesium	ppm	ASTM D5185m		<b>0</b>	0	<1
Calcium	ppm	ASTM D5185m		<b>6</b>	96	4
Phosphorus	ppm	ASTM D5185m	827	<b>512</b>	553	574
Zinc	ppm	ASTM D5185m	0	<b>26</b>	45	21
Sulfur	ppm	ASTM D5185m	13	<b>149</b>	117	14
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	<b>0.12</b>	0.11	0.055
Visc @ 40°C	cSt	ASTM D445	47	<b>46.8</b>	46.6	47.5



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : LEC0048087 **Received** : 16 Apr 2024  
**Lab Number** : 06150225 **Tested** : 17 Apr 2024  
**Unique Number** : 10980303 **Diagnosed** : 18 Apr 2024 - Don Baldrige  
**Test Package** : CONST ( Additional Tests: PQ )

**LESLIE EQUIPMENT COMPANY**  
 105 TENNIS CENTER DR.  
 MARIETTA, OH  
 US 45750-9765  
 Contact: LEANNE KENDALL  
 KendalLeanne@lec1.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
 F: (740)373-5570